# Casingjacks

Casingjacks LLC | sales@casingjack.com

## Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

519 rows; 22 sizes; 314 held; 22 calculated drifts; 15 corrections.

### Where the figures come from

• Every row is an API casing size, weight and grade from our own casing data sheet: outside diameter, nominal weight, grade, wall, inside diameter, drift, collapse, internal yield, joint strength by connection, pipe body yield, capacity and displacement.
• Grades made by a single maker rather than to API, and API rows we could not confirm, are left out. The count left out is printed with each table.

### How we checked them

• Each row was worked through the formulas on our formulas page: wall from the two diameters, pipe body yield from the steel area times the grade's minimum yield, capacity and displacement from the diameters, drift from the inside diameter.
• Where a figure failed a check and a second published figure agreed with the formulas, we corrected it. The corrections list shows the row, the figure, the value on the sheet and the value used.
• Where a figure failed a check and nothing confirmed a correction, the row was held back rather than guessed.

### Reading the tables

• CALC means calculated drift: the sheet left the drift blank, so it is the inside diameter less the API drift allowance (1/8 in below 9-5/8 in; 5/32 in at 9-5/8 in and larger but not above 13-3/8 in; 3/16 in above 13-3/8 in).
• Not recorded means API lists no joint strength for that connection on that row.
• Max pull is the lesser of pipe body yield and the joint strength of the connection, divided by the design factor (1.25 in these tables). With no joint strength listed, the limit uses pipe body yield only, and your connection may be weaker.
• Buoyancy uses steel at 65.5 lb/gal (7,849 kg/m³), with the pipe full of and standing in the same fluid.

Corrections: row, figure, sheet value, value used
8-5/8 in 44# L-80 | Wall in | 5 | 0.5
8-5/8 in 44# N-80 | Wall in | 5 | 0.5
8-5/8 in 44# C-90 | Wall in | 5 | 0.5
8-5/8 in 44# T-95 | Wall in | 5 | 0.5
8-5/8 in 44# C-95 | Wall in | 5 | 0.5
8-5/8 in 44# P-110 | Wall in | 5 | 0.5
8-5/8 in 44# Q-125 | Wall in | 5 | 0.5
4-1/2 in 10.5# M-65 | ID in | 4 | 4.052
4-1/2 in 10.5# M-65 | Capacity bbl/ft | 0.01554 | 0.01595
4-1/2 in 10.5# M-65 | Displacement bbl/ft | 0.00413 | 0.00372
5-1/2 in 17# L-80 | Collapse psi | 6,390 | 6,290
5-1/2 in 17# N-80 | Collapse psi | 6,390 | 6,290
7 in 50.1# T-95 | Collapse psi | 18,810 | 18,180
11-3/4 in 47# M-65 | Body yield lb | 817,000 | 871,000
16 in 109# N-80 | Body yield lb | 1,739,000 | 2,530,000

Check every figure against your own pipe records before you pull.

# Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 1 of 2: size, collapse, body yield and capacity

| OD mm | Weight kg/m | Grade | Wall mm | ID mm | Drift mm | Drift source | Collapse bar | Body yield kN | Capacity m³/m |
|---|---|---|---|---|---|---|---|---|---|
| OD 4-1/2 in | | | | | | | | | |
| 114.3 | 14.14 | J-55 | 5.2 | 103.9 | 100.7 | | 228.2 | 676.1 | 0.00848 |
| 114.3 | 14.14 | K-55 | 5.2 | 103.9 | 100.7 | | 228.2 | 676.1 | 0.00848 |
| 114.3 | 14.14 | M-65 | 5.2 | 103.9 | 100.7 | | 248.2 | 800.7 | 0.00848 |
| 114.3 | 15.63 | J-55 | 5.7 | 102.9 | 99.7 | | 276.5 | 738.4 | 0.00832 |
| 114.3 | 15.63 | K-55 | 5.7 | 102.9 | 99.7 | | 276.5 | 738.4 | 0.00832 |
| 114.3 | 15.63 | M-65 | 5.7 | 102.9 | 99.7 | | 304.7 | 867.4 | 0.00832 |
| 114.3 | 17.26 | J-55 | 6.3 | 101.6 | 98.4 | | 342 | 818.5 | 0.00811 |
| 114.3 | 17.26 | K-55 | 6.3 | 101.6 | 98.4 | | 342 | 818.5 | 0.00811 |
| 114.3 | 17.26 | M-65 | 6.3 | 101.6 | 98.4 | | 383.3 | 965.3 | 0.00811 |
| 114.3 | 17.26 | L-80 | 6.3 | 101.6 | 98.4 | | 437.8 | 1,187.7 | 0.00811 |
| 114.3 | 17.26 | N-80 | 6.3 | 101.6 | 98.4 | | 437.8 | 1,187.7 | 0.00811 |
| 114.3 | 17.26 | C-90 | 6.3 | 101.6 | 98.4 | | 469.5 | 1,334.5 | 0.00811 |
| 114.3 | 17.26 | C-95 | 6.3 | 101.6 | 98.4 | | 484.7 | 1,410.1 | 0.00811 |
| 114.3 | 17.26 | T-95 | 6.3 | 101.6 | 98.4 | | 484.7 | 1,410.1 | 0.00811 |
| 114.3 | 17.26 | P-110 | 6.3 | 101.6 | 98.4 | | 522.6 | 1,632.5 | 0.00811 |
| 114.3 | 20.09 | M-65 | 7.4 | 99.6 | 96.4 | | 503.3 | 1,107.6 | 0.00779 |
| 114.3 | 20.09 | L-80 | 7.4 | 99.6 | 96.4 | | 588.8 | 1,365.6 | 0.00779 |
| 114.3 | 20.09 | N-80 | 7.4 | 99.6 | 96.4 | | 588.8 | 1,365.6 | 0.00779 |
| 114.3 | 20.09 | C-90 | 7.4 | 99.6 | 96.4 | | 641.2 | 1,534.6 | 0.00779 |
| 114.3 | 20.09 | C-95 | 7.4 | 99.6 | 96.4 | | 666 | 1,619.2 | 0.00779 |
| 114.3 | 20.09 | T-95 | 7.4 | 99.6 | 96.4 | | 666 | 1,619.2 | 0.00779 |
| 114.3 | 20.09 | P-110 | 7.4 | 99.6 | 96.4 | | 736.4 | 1,877.1 | 0.00779 |
| 114.3 | 22.47 | L-80 | 8.6 | 97.2 | 94 | | 764.6 | 1,570.2 | 0.00742 |
| 114.3 | 22.47 | P-110 | 8.6 | 97.2 | 94 | | 989.4 | 2,157.4 | 0.00742 |
| 114.3 | 22.47 | Q-125 | 8.6 | 97.2 | 94 | | 1,092.1 | 2,451 | 0.00742 |

Check every figure against your own pipe records before you pull.

# Casingjacks

Casingjacks LLC | sales@casingjack.com

## Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 1 of 2: size, collapse, body yield and capacity

| OD mm | Weight kg/m | Grade | Wall mm | ID mm | Drift mm | Drift source | Collapse bar | Body yield kN | Capacity m³/m |
|---|---|---|---|---|---|---|---|---|---|
| OD 5 in | | | | | | | | | |
| 127 | 17.11 | J-55 | 5.6 | 115.8 | 112.6 | | 211 | 809.6 | 0.01054 |
| 127 | 17.11 | K-55 | 5.6 | 115.8 | 112.6 | | 211 | 809.6 | 0.01054 |
| 127 | 17.11 | M-65 | 5.6 | 115.8 | 112.6 | | 226.8 | 956.4 | 0.01054 |
| 127 | 19.35 | J-55 | 6.4 | 114.1 | 111 | | 285.4 | 925.2 | 0.01023 |
| 127 | 19.35 | K-55 | 6.4 | 114.1 | 111 | | 285.4 | 925.2 | 0.01023 |
| 127 | 19.35 | M-65 | 6.4 | 114.1 | 111 | | 316.5 | 1,089.8 | 0.01023 |
| 127 | 22.32 | J-55 | 7.5 | 112 | 108.8 | | 383.3 | 1,072 | 0.00985 |
| 127 | 22.32 | K-55 | 7.5 | 112 | 108.8 | | 383.3 | 1,072 | 0.00985 |
| 127 | 22.32 | M-65 | 7.5 | 112 | 108.8 | | 433 | 1,263.3 | 0.00985 |
| 127 | 22.32 | L-80 | 7.5 | 112 | 108.8 | | 499.9 | 1,556.9 | 0.00985 |
| 127 | 22.32 | N-80 | 7.5 | 112 | 108.8 | | 499.9 | 1,556.9 | 0.00985 |
| 127 | 22.32 | C-90 | 7.5 | 112 | 108.8 | | 540.5 | 1,752.6 | 0.00985 |
| 127 | 22.32 | C-95 | 7.5 | 112 | 108.8 | | 559.2 | 1,850.5 | 0.00985 |
| 127 | 22.32 | T-95 | 7.5 | 112 | 108.8 | | 559.2 | 1,850.5 | 0.00985 |
| 127 | 22.32 | P-110 | 7.5 | 112 | 108.8 | | 610.2 | 2,139.6 | 0.00985 |
| 127 | 26.79 | M-65 | 9.2 | 108.6 | 105.4 | | 601.9 | 1,525.7 | 0.00926 |
| 127 | 26.79 | L-80 | 9.2 | 108.6 | 105.4 | | 723.9 | 1,877.1 | 0.00926 |
| 127 | 26.79 | N-80 | 9.2 | 108.6 | 105.4 | | 723.9 | 1,877.1 | 0.00926 |
| 127 | 26.79 | C-90 | 9.2 | 108.6 | 105.4 | | 795 | 2,112.9 | 0.00926 |
| 127 | 26.79 | C-95 | 9.2 | 108.6 | 105.4 | | 829.4 | 2,228.6 | 0.00926 |
| 127 | 26.79 | T-95 | 9.2 | 108.6 | 105.4 | | 829.4 | 2,228.6 | 0.00926 |
| 127 | 26.79 | P-110 | 9.2 | 108.6 | 105.4 | | 928.7 | 2,580 | 0.00926 |
| 127 | 26.79 | Q-125 | 9.2 | 108.6 | 105.4 | | 1,022.5 | 2,931.4 | 0.00926 |
| 127 | 31.85 | L-80 | 11.1 | 104.8 | 101.6 | | 879.8 | 2,228.6 | 0.00863 |
| 127 | 31.85 | N-80 | 11.1 | 104.8 | 101.6 | | 879.8 | 2,228.6 | 0.00863 |

Check every figure against your own pipe records before you pull.

# Casingjacks

Casingjacks LLC | sales@casingjack.com

## Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 1 of 2: size, collapse, body yield and capacity

| OD mm | Weight kg/m | Grade | Wall mm | ID mm | Drift mm | Drift source | Collapse bar | Body yield kN | Capacity m³/m |
|---|---|---|---|---|---|---|---|---|---|
| OD 5 in | | | | | | | | | |
| 127 | 31.85 | C-90 | 11.1 | 104.8 | 101.6 | | 990.1 | 2,508.8 | 0.00863 |
| 127 | 31.85 | C-95 | 11.1 | 104.8 | 101.6 | | 1,045.2 | 2,646.7 | 0.00863 |
| 127 | 31.85 | T-95 | 11.1 | 104.8 | 101.6 | | 1,045.2 | 2,646.7 | 0.00863 |
| 127 | 31.85 | P-110 | 11.1 | 104.8 | 101.6 | | 1,210 | 3,064.8 | 0.00863 |
| 127 | 31.85 | Q-125 | 11.1 | 104.8 | 101.6 | | 1,374.8 | 3,483 | 0.00863 |
| 127 | 34.53 | L-80 | 12.1 | 102.7 | 99.5 | | 953.5 | 2,415.4 | 0.00829 |
| 127 | 34.53 | N-80 | 12.1 | 102.7 | 99.5 | | 953.5 | 2,415.4 | 0.00829 |
| 127 | 34.53 | C-90 | 12.1 | 102.7 | 99.5 | | 1,072.8 | 2,717.9 | 0.00829 |
| 127 | 34.53 | C-95 | 12.1 | 102.7 | 99.5 | | 1,132.8 | 2,869.1 | 0.00829 |
| 127 | 34.53 | T-95 | 12.1 | 102.7 | 99.5 | | 1,132.8 | 2,869.1 | 0.00829 |
| 127 | 34.53 | P-110 | 12.1 | 102.7 | 99.5 | | 1,311.4 | 3,322.8 | 0.00829 |
| 127 | 34.53 | Q-125 | 12.1 | 102.7 | 99.5 | | 1,490.6 | 3,776.5 | 0.00829 |
| 127 | 35.86 | L-80 | 12.7 | 101.6 | 98.4 | | 992.8 | 2,517.7 | 0.00811 |
| 127 | 35.86 | N-80 | 12.7 | 101.6 | 98.4 | | 992.8 | 2,517.7 | 0.00811 |
| 127 | 35.86 | C-90 | 12.7 | 101.6 | 98.4 | | 1,117 | 2,829.1 | 0.00811 |
| 127 | 35.86 | C-95 | 12.7 | 101.6 | 98.4 | | 1,179 | 2,989.2 | 0.00811 |
| 127 | 35.86 | T-95 | 12.7 | 101.6 | 98.4 | | 1,179 | 2,989.2 | 0.00811 |
| 127 | 35.86 | P-110 | 12.7 | 101.6 | 98.4 | | 1,365.2 | 3,460.7 | 0.00811 |
| 127 | 35.86 | Q-125 | 12.7 | 101.6 | 98.4 | | 1,551.3 | 3,932.2 | 0.00811 |
| OD 5-1/2 in | | | | | | | | | |
| 139.7 | 23.07 | J-55 | 7 | 125.7 | 122.6 | | 278.5 | 1,103.2 | 0.01242 |
| 139.7 | 23.07 | K-55 | 7 | 125.7 | 122.6 | | 278.5 | 1,103.2 | 0.01242 |
| 139.7 | 23.07 | M-65 | 7 | 125.7 | 122.6 | | 308.2 | 1,303.3 | 0.01242 |
| 139.7 | 25.3 | J-55 | 7.7 | 124.3 | 121.1 | | 338.5 | 1,214.4 | 0.01213 |
| 139.7 | 25.3 | K-55 | 7.7 | 124.3 | 121.1 | | 338.5 | 1,214.4 | 0.01213 |

Check every figure against your own pipe records before you pull.

# Casingjacks

Casingjacks LLC | sales@casingjack.com

## Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 1 of 2: size, collapse, body yield and capacity

| OD mm | Weight kg/m | Grade | Wall mm | ID mm | Drift mm | Drift source | Collapse bar | Body yield kN | Capacity m³/m |
|---|---|---|---|---|---|---|---|---|---|
| OD 5-1/2 in | | | | | | | | | |
| 139.7 | 25.3 | M-65 | 7.7 | 124.3 | 121.1 | | 379.9 | 1,436.8 | 0.01213 |
| 139.7 | 25.3 | L-80 | 7.7 | 124.3 | 121.1 | | 433.7 | 1,765.9 | 0.01213 |
| 139.7 | 25.3 | N-80 | 7.7 | 124.3 | 121.1 | | 433.7 | 1,765.9 | 0.01213 |
| 139.7 | 25.3 | C-90 | 7.7 | 124.3 | 121.1 | | 464.7 | 1,988.4 | 0.01213 |
| 139.7 | 25.3 | C-95 | 7.7 | 124.3 | 121.1 | | 478.5 | 2,095.1 | 0.01213 |
| 139.7 | 25.3 | T-95 | 7.7 | 124.3 | 121.1 | | 478.5 | 2,095.1 | 0.01213 |
| 139.7 | 25.3 | P-110 | 7.7 | 124.3 | 121.1 | | 515.7 | 2,428.7 | 0.01213 |
| 139.7 | 25.3 | Q-125 | 7.7 | 124.3 | 121.1 | | 544 | 2,757.9 | 0.01213 |
| 139.7 | 29.76 | M-65 | 9.2 | 121.4 | 118.2 | | 519.9 | 1,685.9 | 0.01157 |
| 139.7 | 29.76 | L-80 | 9.2 | 121.4 | 118.2 | | 608.8 | 2,072.9 | 0.01157 |
| 139.7 | 29.76 | N-80 | 9.2 | 121.4 | 118.2 | | 608.8 | 2,072.9 | 0.01157 |
| 139.7 | 29.76 | C-90 | 9.2 | 121.4 | 118.2 | | 664 | 2,335.3 | 0.01157 |
| 139.7 | 29.76 | C-95 | 9.2 | 121.4 | 118.2 | | 690.2 | 2,464.3 | 0.01157 |
| 139.7 | 29.76 | T-95 | 9.2 | 121.4 | 118.2 | | 690.2 | 2,464.3 | 0.01157 |
| 139.7 | 29.76 | P-110 | 9.2 | 121.4 | 118.2 | | 765.3 | 2,851.3 | 0.01157 |
| 139.7 | 29.76 | Q-125 | 9.2 | 121.4 | 118.2 | | 832.9 | 3,242.8 | 0.01157 |
| 139.7 | 34.23 | L-80 | 10.5 | 118.6 | 115.4 | | 769.5 | 2,357.6 | 0.01105 |
| 139.7 | 34.23 | N-80 | 10.5 | 118.6 | 115.4 | | 769.5 | 2,357.6 | 0.01105 |
| 139.7 | 34.23 | C-90 | 10.5 | 118.6 | 115.4 | | 853.6 | 2,655.6 | 0.01105 |
| 139.7 | 34.23 | C-95 | 10.5 | 118.6 | 115.4 | | 892.2 | 2,802.4 | 0.01105 |
| 139.7 | 34.23 | T-95 | 10.5 | 118.6 | 115.4 | | 892.2 | 2,802.4 | 0.01105 |
| 139.7 | 34.23 | P-110 | 10.5 | 118.6 | 115.4 | | 1,002.5 | 3,242.8 | 0.01105 |
| 139.7 | 34.23 | Q-125 | 10.5 | 118.6 | 115.4 | | 1,108 | 3,687.6 | 0.01105 |
| 139.7 | 38.69 | C-90 | 12.1 | 115.5 | 112.3 | | 981.8 | 3,007 | 0.01048 |
| 139.7 | 38.69 | C-95 | 12.1 | 115.5 | 112.3 | | 1,036.3 | 3,176 | 0.01048 |

Check every figure against your own pipe records before you pull.

# Casingjacks

Casingjacks LLC | sales@casingjack.com

## Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 1 of 2: size, collapse, body yield and capacity

| OD mm | Weight kg/m | Grade | Wall mm | ID mm | Drift mm | Drift source | Collapse bar | Body yield kN | Capacity m³/m |
|---|---|---|---|---|---|---|---|---|---|
| OD 5-1/2 in | | | | | | | | | |
| 139.7 | 38.69 | T-95 | 12.1 | 115.5 | 112.3 | | 1,036.3 | 3,176 | 0.01048 |
| 139.7 | 38.69 | P-110 | 12.1 | 115.5 | 112.3 | | 1,199.7 | 3,674.2 | 0.01048 |
| 139.7 | 38.69 | Q-125 | 12.1 | 115.5 | 112.3 | | 1,363.1 | 4,176.9 | 0.01048 |
| 139.7 | 39.88 | C-90 | 12.7 | 114.3 | 111.1 | | 1,025.9 | 3,144.9 | 0.01026 |
| 139.7 | 39.88 | T-95 | 12.7 | 114.3 | 111.1 | | 1,082.5 | 3,318.4 | 0.01026 |
| 139.7 | 44.2 | C-90 | 14.3 | 111.2 | 108 | | 1,138.3 | 3,491.9 | 0.0097 |
| 139.7 | 44.2 | T-95 | 14.3 | 111.2 | 108 | | 1,201.8 | 3,683.1 | 0.0097 |
| 139.7 | 48.51 | C-90 | 15.9 | 107.9 | 104.8 | | 1,250 | 3,829.9 | 0.00915 |
| 139.7 | 48.51 | T-95 | 15.9 | 107.9 | 104.8 | | 1,319.7 | 4,043.4 | 0.00915 |
| 139.7 | 52.53 | C-90 | 17.4 | 104.8 | 101.6 | | 1,356.9 | 4,159.1 | 0.00863 |
| 139.7 | 52.53 | T-95 | 17.4 | 104.8 | 101.6 | | 1,431.4 | 4,390.4 | 0.00863 |
| 139.7 | 56.55 | C-90 | 19 | 101.6 | 98.4 | | 1,461.7 | 4,479.4 | 0.00811 |
| 139.7 | 56.55 | T-95 | 19 | 101.6 | 98.4 | | 1,543 | 4,728.5 | 0.00811 |
| 139.7 | 60.27 | C-90 | 20.6 | 98.5 | 95.3 | | 1,561.7 | 4,786.3 | 0.00761 |
| 139.7 | 60.27 | T-95 | 20.6 | 98.5 | 95.3 | | 1,649.2 | 5,053.2 | 0.00761 |
| 139.7 | 64.14 | C-90 | 22.2 | 95.3 | 92.1 | | 1,660.3 | 5,088.8 | 0.00713 |
| 139.7 | 64.14 | T-95 | 22.2 | 95.3 | 92.1 | | 1,751.3 | 5,373.5 | 0.00713 |
| OD 5-5/8 in | | | | | | | | | |
| 142.9 | 39.73 | L-80 | 12.1 | 118.6 | 115.5 | CALC | 856.3 | 2,744.6 | 0.01106 |
| 142.9 | 39.73 | P-110 | 12.1 | 118.6 | 115.5 | CALC | 1,177.6 | 3,776.5 | 0.01106 |
| OD 5-3/4 in | | | | | | | | | |
| 146 | 26.94 | J-55 | 7.7 | 130.6 | 127.4 | CALC | 311.6 | 1,272.2 | 0.0134 |
| 146 | 26.94 | L-80 | 7.7 | 130.6 | 127.4 | CALC | 393 | 1,850.5 | 0.0134 |
| 146 | 26.94 | N-80 | 7.7 | 130.6 | 127.4 | CALC | 393 | 1,850.5 | 0.0134 |
| 146 | 26.94 | P-110 | 7.7 | 130.6 | 127.4 | CALC | 457.8 | 2,544.4 | 0.0134 |

Check every figure against your own pipe records before you pull.

# Casingjacks

Casingjacks LLC | sales@casingjack.com

## Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 1 of 2: size, collapse, body yield and capacity

| OD mm | Weight kg/m | Grade | Wall mm | ID mm | Drift mm | Drift source | Collapse bar | Body yield kN | Capacity m³/m |
|---|---|---|---|---|---|---|---|---|---|
| OD 5-3/4 in | | | | | | | | | |
| 146 | 29.32 | J-55 | 8.5 | 129 | 125.9 | CALC | 373 | 1,392.3 | 0.01308 |
| 146 | 29.32 | L-80 | 8.5 | 129 | 125.9 | CALC | 484.7 | 2,028.4 | 0.01308 |
| 146 | 29.32 | N-80 | 8.5 | 129 | 125.9 | CALC | 484.7 | 2,028.4 | 0.01308 |
| 146 | 29.32 | P-110 | 8.5 | 129 | 125.9 | CALC | 588.1 | 2,789 | 0.01308 |
| 146 | 32.44 | L-80 | 9.5 | 127 | 123.8 | CALC | 602.6 | 2,255.2 | 0.01267 |
| 146 | 32.44 | N-80 | 9.5 | 127 | 123.8 | CALC | 602.6 | 2,255.2 | 0.01267 |
| 146 | 32.44 | P-110 | 9.5 | 127 | 123.8 | CALC | 755.7 | 3,100.4 | 0.01267 |
| 146 | 36.01 | L-80 | 10.7 | 124.7 | 121.5 | CALC | 734.3 | 2,504.3 | 0.01222 |
| 146 | 36.01 | N-80 | 10.7 | 124.7 | 121.5 | CALC | 734.3 | 2,504.3 | 0.01222 |
| 146 | 36.01 | P-110 | 10.7 | 124.7 | 121.5 | CALC | 944.6 | 3,442.9 | 0.01222 |
| OD 6-5/8 in | | | | | | | | | |
| 168.3 | 29.76 | H-40 | 7.3 | 153.6 | 150.5 | | 173.7 | 1,018.6 | 0.01854 |
| 168.3 | 29.76 | J-55 | 7.3 | 153.6 | 150.5 | | 204.8 | 1,401.2 | 0.01854 |
| 168.3 | 29.76 | K-55 | 7.3 | 153.6 | 150.5 | | 204.8 | 1,401.2 | 0.01854 |
| 168.3 | 29.76 | M-65 | 7.3 | 153.6 | 150.5 | | 219.9 | 1,659.2 | 0.01854 |
| 168.3 | 35.72 | J-55 | 8.9 | 150.4 | 147.2 | | 314.4 | 1,699.2 | 0.01776 |
| 168.3 | 35.72 | K-55 | 8.9 | 150.4 | 147.2 | | 314.4 | 1,699.2 | 0.01776 |
| 168.3 | 35.72 | M-65 | 8.9 | 150.4 | 147.2 | | 350.3 | 2,006.1 | 0.01776 |
| 168.3 | 35.72 | L-80 | 8.9 | 150.4 | 147.2 | | 397.1 | 2,468.8 | 0.01776 |
| 168.3 | 35.72 | C-90 | 8.9 | 150.4 | 147.2 | | 423.3 | 2,775.7 | 0.01776 |
| 168.3 | 35.72 | C-95 | 8.9 | 150.4 | 147.2 | | 435.1 | 2,931.4 | 0.01776 |
| 168.3 | 35.72 | P-110 | 8.9 | 150.4 | 147.2 | | 464 | 3,394 | 0.01776 |
| 168.3 | 41.67 | M-65 | 10.6 | 147.1 | 143.9 | | 483.3 | 2,353.1 | 0.01699 |
| 168.3 | 41.67 | L-80 | 10.6 | 147.1 | 143.9 | | 563.3 | 2,895.8 | 0.01699 |
| 168.3 | 41.67 | N-80 | 10.6 | 147.1 | 143.9 | | 563.3 | 2,895.8 | 0.01699 |

Check every figure against your own pipe records before you pull.

# Casingjacks

Casingjacks LLC | sales@casingjack.com

## Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 1 of 2: size, collapse, body yield and capacity

| OD mm | Weight kg/m | Grade | Wall mm | ID mm | Drift mm | Drift source | Collapse bar | Body yield kN | Capacity m³/m |
|---|---|---|---|---|---|---|---|---|---|
| OD 6-5/8 in | | | | | | | | | |
| 168.3 | 41.67 | C-90 | 10.6 | 147.1 | 143.9 | | 612.3 | 3,256.1 | 0.01699 |
| 168.3 | 41.67 | C-95 | 10.6 | 147.1 | 143.9 | | 635.7 | 3,438.5 | 0.01699 |
| 168.3 | 41.67 | P-110 | 10.6 | 147.1 | 143.9 | | 700.5 | 3,981.2 | 0.01699 |
| 168.3 | 47.62 | L-80 | 12.1 | 144.1 | 141 | | 711.5 | 3,265 | 0.01632 |
| 168.3 | 47.62 | N-80 | 12.1 | 144.1 | 141 | | 711.5 | 3,265 | 0.01632 |
| 168.3 | 47.62 | C-90 | 12.1 | 144.1 | 141 | | 781.2 | 3,674.2 | 0.01632 |
| 168.3 | 47.62 | C-95 | 12.1 | 144.1 | 141 | | 814.3 | 3,878.8 | 0.01632 |
| 168.3 | 47.62 | P-110 | 12.1 | 144.1 | 141 | | 911.5 | 4,488.3 | 0.01632 |
| 168.3 | 47.62 | Q-125 | 12.1 | 144.1 | 141 | | 1,001.8 | 5,102.1 | 0.01632 |
| OD 7 in | | | | | | | | | |
| 177.8 | 29.76 | H-40 | 6.9 | 164 | 160.8 | | 135.8 | 1,023.1 | 0.02112 |
| 177.8 | 29.76 | J-55 | 6.9 | 164 | 160.8 | | 156.5 | 1,405.6 | 0.02112 |
| 177.8 | 29.76 | K-55 | 6.9 | 164 | 160.8 | | 156.5 | 1,405.6 | 0.02112 |
| 177.8 | 29.76 | M-65 | 6.9 | 164 | 160.8 | | 171 | 1,663.6 | 0.02112 |
| 177.8 | 34.23 | J-55 | 8.1 | 161.7 | 158.5 | | 225.5 | 1,628 | 0.02054 |
| 177.8 | 34.23 | K-55 | 8.1 | 161.7 | 158.5 | | 225.5 | 1,628 | 0.02054 |
| 177.8 | 34.23 | M-65 | 8.1 | 161.7 | 158.5 | | 244.1 | 1,926.1 | 0.02054 |
| 177.8 | 34.23 | L-80 | 8.1 | 161.7 | 158.5 | | 264.1 | 2,366.5 | 0.02054 |
| 177.8 | 34.23 | N-80 | 8.1 | 161.7 | 158.5 | | 264.1 | 2,366.5 | 0.02054 |
| 177.8 | 34.23 | C-90 | 8.1 | 161.7 | 158.5 | | 277.9 | 2,664.5 | 0.02054 |
| 177.8 | 34.23 | C-95 | 8.1 | 161.7 | 158.5 | | 285.4 | 2,811.3 | 0.02054 |
| 177.8 | 34.23 | T-95 | 8.1 | 161.7 | 158.5 | | 285.4 | 2,811.3 | 0.02054 |
| 177.8 | 38.69 | J-55 | 9.2 | 159.4 | 156.2 | | 297.9 | 1,846 | 0.01996 |
| 177.8 | 38.69 | K-55 | 9.2 | 159.4 | 156.2 | | 297.9 | 1,846 | 0.01996 |
| 177.8 | 38.69 | M-65 | 9.2 | 159.4 | 156.2 | | 330.9 | 2,184.1 | 0.01996 |

Check every figure against your own pipe records before you pull.

# Casingjacks

Casingjacks LLC | sales@casingjack.com

## Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 1 of 2: size, collapse, body yield and capacity

| OD mm | Weight kg/m | Grade | Wall mm | ID mm | Drift mm | Drift source | Collapse bar | Body yield kN | Capacity m³/m |
|---|---|---|---|---|---|---|---|---|---|
| OD 7 in | | | | | | | | | |
| 177.8 | 38.69 | L-80 | 9.2 | 159.4 | 156.2 | | 373 | 2,686.7 | 0.01996 |
| 177.8 | 38.69 | N-80 | 9.2 | 159.4 | 156.2 | | 373 | 2,686.7 | 0.01996 |
| 177.8 | 38.69 | C-90 | 9.2 | 159.4 | 156.2 | | 395.8 | 3,020.3 | 0.01996 |
| 177.8 | 38.69 | C-95 | 9.2 | 159.4 | 156.2 | | 405.4 | 3,189.4 | 0.01996 |
| 177.8 | 38.69 | T-95 | 9.2 | 159.4 | 156.2 | | 405.4 | 3,189.4 | 0.01996 |
| 177.8 | 38.69 | P-110 | 9.2 | 159.4 | 156.2 | | 429.5 | 3,692 | 0.01996 |
| 177.8 | 43.16 | M-65 | 10.4 | 157.1 | 153.9 | | 419.9 | 2,442.1 | 0.01938 |
| 177.8 | 43.16 | L-80 | 10.4 | 157.1 | 153.9 | | 484 | 3,007 | 0.01938 |
| 177.8 | 43.16 | N-80 | 10.4 | 157.1 | 153.9 | | 484 | 3,007 | 0.01938 |
| 177.8 | 43.16 | C-90 | 10.4 | 157.1 | 153.9 | | 522.6 | 3,380.6 | 0.01938 |
| 177.8 | 43.16 | C-95 | 10.4 | 157.1 | 153.9 | | 539.9 | 3,571.9 | 0.01938 |
| 177.8 | 43.16 | T-95 | 10.4 | 157.1 | 153.9 | | 539.9 | 3,571.9 | 0.01938 |
| 177.8 | 43.16 | P-110 | 10.4 | 157.1 | 153.9 | | 588.1 | 4,132.4 | 0.01938 |
| 177.8 | 43.16 | Q-125 | 10.4 | 157.1 | 153.9 | | 627.4 | 4,697.3 | 0.01938 |
| 177.8 | 47.62 | L-80 | 11.5 | 154.8 | 151.6 | | 593.6 | 3,313.9 | 0.01882 |
| 177.8 | 47.62 | N-80 | 11.5 | 154.8 | 151.6 | | 593.6 | 3,313.9 | 0.01882 |
| 177.8 | 47.62 | C-90 | 11.5 | 154.8 | 151.6 | | 646.7 | 3,732.1 | 0.01882 |
| 177.8 | 47.62 | C-95 | 11.5 | 154.8 | 151.6 | | 672.2 | 3,936.7 | 0.01882 |
| 177.8 | 47.62 | T-95 | 11.5 | 154.8 | 151.6 | | 672.2 | 3,936.7 | 0.01882 |
| 177.8 | 47.62 | P-110 | 11.5 | 154.8 | 151.6 | | 743.3 | 4,559.4 | 0.01882 |
| 177.8 | 47.62 | Q-125 | 11.5 | 154.8 | 151.6 | | 808.1 | 5,182.2 | 0.01882 |
| 177.8 | 52.09 | L-80 | 12.6 | 152.5 | 149.3 | | 701.9 | 3,620.9 | 0.01827 |
| 177.8 | 52.09 | N-80 | 12.6 | 152.5 | 149.3 | | 701.9 | 3,620.9 | 0.01827 |
| 177.8 | 52.09 | C-90 | 12.6 | 152.5 | 149.3 | | 770.1 | 4,070.1 | 0.01827 |
| 177.8 | 52.09 | C-95 | 12.6 | 152.5 | 149.3 | | 803.2 | 4,297 | 0.01827 |

Check every figure against your own pipe records before you pull.

# Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 1 of 2: size, collapse, body yield and capacity

| OD mm | Weight kg/m | Grade | Wall mm | ID mm | Drift mm | Drift source | Collapse bar | Body yield kN | Capacity m³/m |
|---|---|---|---|---|---|---|---|---|---|
| OD 7 in | | | | | | | | | |
| 177.8 | 52.09 | T-95 | 12.6 | 152.5 | 149.3 | | 803.2 | 4,297 | 0.01827 |
| 177.8 | 52.09 | P-110 | 12.6 | 152.5 | 149.3 | | 897.7 | 4,977.6 | 0.01827 |
| 177.8 | 52.09 | Q-125 | 12.6 | 152.5 | 149.3 | | 986.6 | 5,658.1 | 0.01827 |
| 177.8 | 56.55 | L-80 | 13.7 | 150.4 | 147.2 | | 785.3 | 3,901.1 | 0.01776 |
| 177.8 | 56.55 | N-80 | 13.7 | 150.4 | 147.2 | | 785.3 | 3,901.1 | 0.01776 |
| 177.8 | 56.55 | C-90 | 13.7 | 150.4 | 147.2 | | 883.9 | 4,385.9 | 0.01776 |
| 177.8 | 56.55 | C-95 | 13.7 | 150.4 | 147.2 | | 926.7 | 4,630.6 | 0.01776 |
| 177.8 | 56.55 | T-95 | 13.7 | 150.4 | 147.2 | | 926.7 | 4,630.6 | 0.01776 |
| 177.8 | 56.55 | P-110 | 13.7 | 150.4 | 147.2 | | 1,043.9 | 5,360.1 | 0.01776 |
| 177.8 | 56.55 | Q-125 | 13.7 | 150.4 | 147.2 | | 1,154.9 | 6,094.1 | 0.01776 |
| 177.8 | 61.01 | C-90 | 15 | 147.8 | 144.7 | | 958.4 | 4,755.1 | 0.01716 |
| 177.8 | 61.01 | T-95 | 15 | 147.8 | 144.7 | | 1,011.5 | 5,022 | 0.01716 |
| 177.8 | 61.01 | P-110 | 15 | 147.8 | 144.7 | | 1,171.4 | 5,813.8 | 0.01716 |
| 177.8 | 61.01 | Q-125 | 15 | 147.8 | 144.7 | | 1,330.7 | 6,605.6 | 0.01716 |
| 177.8 | 63.54 | C-90 | 15.9 | 146 | 142.9 | | 1,009.4 | 5,013.1 | 0.01675 |
| 177.8 | 63.54 | T-95 | 15.9 | 146 | 142.9 | | 1,065.2 | 5,288.9 | 0.01675 |
| 177.8 | 69.05 | C-90 | 17.4 | 142.9 | 139.7 | | 1,098.3 | 5,453.5 | 0.01604 |
| 177.8 | 69.05 | T-95 | 17.4 | 142.9 | 139.7 | | 1,159.7 | 5,756 | 0.01604 |
| 177.8 | 74.56 | C-90 | 19 | 139.7 | 136.5 | | 1,187.3 | 5,893.9 | 0.01533 |
| 177.8 | 74.56 | T-95 | 19 | 139.7 | 136.5 | | 1,253.5 | 6,223.1 | 0.01533 |
| 177.8 | 79.77 | C-90 | 20.6 | 136.6 | 133.4 | | 1,272.8 | 6,320.9 | 0.01464 |
| 177.8 | 79.77 | T-95 | 20.6 | 136.6 | 133.4 | | 1,343.1 | 6,672.3 | 0.01464 |
| 177.8 | 84.97 | C-90 | 22.2 | 133.3 | 130.2 | | 1,357.6 | 6,739.1 | 0.01397 |
| 177.8 | 84.97 | T-95 | 22.2 | 133.3 | 130.2 | | 1,432.7 | 7,117.2 | 0.01397 |

# Casingjacks

Casingjacks LLC | sales@casingjack.com

## Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 1 of 2: size, collapse, body yield and capacity

| OD mm | Weight kg/m | Grade | Wall mm | ID mm | Drift mm | Drift source | Collapse bar | Body yield kN | Capacity m³/m |
|---|---|---|---|---|---|---|---|---|---|
| OD 7-5/8 in | | | | | | | | | |
| 193.7 | 35.72 | H-40 | 7.6 | 178.4 | 175.3 | | 140 | 1,227.7 | 0.02501 |
| 193.7 | 39.29 | J-55 | 8.3 | 177 | 173.8 | | 199.3 | 1,841.6 | 0.02461 |
| 193.7 | 39.29 | K-55 | 8.3 | 177 | 173.8 | | 199.3 | 1,841.6 | 0.02461 |
| 193.7 | 39.29 | M-65 | 8.3 | 177 | 173.8 | | 213.7 | 2,175.2 | 0.02461 |
| 193.7 | 39.29 | L-80 | 8.3 | 177 | 173.8 | | 234.4 | 2,677.8 | 0.02461 |
| 193.7 | 39.29 | N-80 | 8.3 | 177 | 173.8 | | 234.4 | 2,677.8 | 0.02461 |
| 193.7 | 39.29 | C-90 | 8.3 | 177 | 173.8 | | 248.9 | 3,011.4 | 0.02461 |
| 193.7 | 39.29 | C-95 | 8.3 | 177 | 173.8 | | 255.8 | 3,176 | 0.02461 |
| 193.7 | 39.29 | T-95 | 8.3 | 177 | 173.8 | | 255.8 | 3,176 | 0.02461 |
| 193.7 | 39.29 | P-110 | 8.3 | 177 | 173.8 | | 270.3 | 3,678.7 | 0.02461 |
| 193.7 | 44.2 | M-65 | 9.5 | 174.6 | 171.4 | | 297.2 | 2,468.8 | 0.02395 |
| 193.7 | 44.2 | L-80 | 9.5 | 174.6 | 171.4 | | 330.3 | 3,038.1 | 0.02395 |
| 193.7 | 44.2 | N-80 | 9.5 | 174.6 | 171.4 | | 330.3 | 3,038.1 | 0.02395 |
| 193.7 | 44.2 | C-90 | 9.5 | 174.6 | 171.4 | | 347.5 | 3,420.7 | 0.02395 |
| 193.7 | 44.2 | C-95 | 9.5 | 174.6 | 171.4 | | 354.4 | 3,607.5 | 0.02395 |
| 193.7 | 44.2 | T-95 | 9.5 | 174.6 | 171.4 | | 354.4 | 3,607.5 | 0.02395 |
| 193.7 | 44.2 | P-110 | 9.5 | 174.6 | 171.4 | | 368.9 | 4,181.3 | 0.02395 |
| 193.7 | 50.15 | L-80 | 10.9 | 171.8 | 168.7 | | 452.3 | 3,460.7 | 0.02319 |
| 193.7 | 50.15 | N-80 | 10.9 | 171.8 | 168.7 | | 452.3 | 3,460.7 | 0.02319 |
| 193.7 | 50.15 | C-90 | 10.9 | 171.8 | 168.7 | | 486.1 | 3,892.2 | 0.02319 |
| 193.7 | 50.15 | C-95 | 10.9 | 171.8 | 168.7 | | 501.9 | 4,105.7 | 0.02319 |
| 193.7 | 50.15 | T-95 | 10.9 | 171.8 | 168.7 | | 501.9 | 4,105.7 | 0.02319 |
| 193.7 | 50.15 | P-110 | 10.9 | 171.8 | 168.7 | | 542.6 | 4,755.1 | 0.02319 |
| 193.7 | 50.15 | Q-125 | 10.9 | 171.8 | 168.7 | | 575.7 | 5,404.6 | 0.02319 |
| 193.7 | 58.04 | L-80 | 12.7 | 168.3 | 165.1 | | 608.1 | 3,981.2 | 0.02224 |

# Casingjacks

Casingjacks LLC | sales@casingjack.com

## Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 1 of 2: size, collapse, body yield and capacity

| OD mm | Weight kg/m | Grade | Wall mm | ID mm | Drift mm | Drift source | Collapse bar | Body yield kN | Capacity m³/m |
|---|---|---|---|---|---|---|---|---|---|
| OD 7-5/8 in | | | | | | | | | |
| 193.7 | 58.04 | N-80 | 12.7 | 168.3 | 165.1 | | 608.1 | 3,981.2 | 0.02224 |
| 193.7 | 58.04 | C-90 | 12.7 | 168.3 | 165.1 | | 663.3 | 4,479.4 | 0.02224 |
| 193.7 | 58.04 | C-95 | 12.7 | 168.3 | 165.1 | | 689.5 | 4,728.5 | 0.02224 |
| 193.7 | 58.04 | T-95 | 12.7 | 168.3 | 165.1 | | 689.5 | 4,728.5 | 0.02224 |
| 193.7 | 58.04 | P-110 | 12.7 | 168.3 | 165.1 | | 763.9 | 5,475.8 | 0.02224 |
| 193.7 | 58.04 | Q-125 | 12.7 | 168.3 | 165.1 | | 831.5 | 6,223.1 | 0.02224 |
| 193.7 | 63.69 | L-80 | 14.3 | 165.1 | 162 | | 745.3 | 4,439.3 | 0.02142 |
| 193.7 | 63.69 | N-80 | 14.3 | 165.1 | 162 | | 745.3 | 4,439.3 | 0.02142 |
| 193.7 | 63.69 | C-90 | 14.3 | 165.1 | 162 | | 819.8 | 4,990.9 | 0.02142 |
| 193.7 | 63.69 | C-95 | 14.3 | 165.1 | 162 | | 855.6 | 5,271.1 | 0.02142 |
| 193.7 | 63.69 | T-95 | 14.3 | 165.1 | 162 | | 855.6 | 5,271.1 | 0.02142 |
| 193.7 | 63.69 | P-110 | 14.3 | 165.1 | 162 | | 959.8 | 6,103 | 0.02142 |
| 193.7 | 63.69 | Q-125 | 14.3 | 165.1 | 162 | | 1,058.3 | 6,934.8 | 0.02142 |
| 193.7 | 67.41 | L-80 | 15.1 | 163.4 | 160.3 | | 793.6 | 4,675.1 | 0.02098 |
| 193.7 | 67.41 | N-80 | 15.1 | 163.4 | 160.3 | | 793.6 | 4,675.1 | 0.02098 |
| 193.7 | 67.41 | C-90 | 15.1 | 163.4 | 160.3 | | 892.9 | 5,262.2 | 0.02098 |
| 193.7 | 67.41 | C-95 | 15.1 | 163.4 | 160.3 | | 941.8 | 5,551.4 | 0.02098 |
| 193.7 | 67.41 | P-110 | 15.1 | 163.4 | 160.3 | | 1,063.9 | 6,432.1 | 0.02098 |
| 193.7 | 67.41 | Q-125 | 15.1 | 163.4 | 160.3 | | 1,178.3 | 7,308.4 | 0.02098 |
| 193.7 | 70.09 | L-80 | 15.9 | 161.9 | 158.8 | | 830.1 | 4,893 | 0.02059 |
| 193.7 | 70.09 | N-80 | 15.9 | 161.9 | 158.8 | | 830.1 | 4,893 | 0.02059 |
| 193.7 | 70.09 | C-90 | 15.9 | 161.9 | 158.8 | | 933.6 | 5,502.5 | 0.02059 |
| 193.7 | 70.09 | C-95 | 15.9 | 161.9 | 158.8 | | 986 | 5,809.4 | 0.02059 |
| 193.7 | 70.09 | T-95 | 15.9 | 161.9 | 158.8 | | 986 | 5,809.4 | 0.02059 |
| 193.7 | 70.09 | P-110 | 15.9 | 161.9 | 158.8 | | 1,141.1 | 6,725.7 | 0.02059 |

Check every figure against your own pipe records before you pull.

# Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 1 of 2: size, collapse, body yield and capacity

| OD mm | Weight kg/m | Grade | Wall mm | ID mm | Drift mm | Drift source | Collapse bar | Body yield kN | Capacity m³/m |
|---|---|---|---|---|---|---|---|---|---|
| OD 7-5/8 in | | | | | | | | | |
| 193.7 | 70.09 | Q-125 | 15.9 | 161.9 | 158.8 | | 1,289.3 | 7,642 | 0.02059 |
| 193.7 | 76.19 | C-90 | 17.4 | 158.8 | 155.6 | | 1,017.7 | 5,996.2 | 0.0198 |
| 193.7 | 76.19 | T-95 | 17.4 | 158.8 | 155.6 | | 1,074.2 | 6,329.8 | 0.0198 |
| 193.7 | 82.3 | C-90 | 19 | 155.6 | 152.4 | | 1,100.4 | 6,485.5 | 0.01901 |
| 193.7 | 82.3 | T-95 | 19 | 155.6 | 152.4 | | 1,161.8 | 6,845.8 | 0.01901 |
| OD 7-3/4 in | | | | | | | | | |
| 196.8 | 68.6 | L-80 | 15.1 | 166.6 | 163.4 | | 781.9 | 4,759.6 | 0.02181 |
| 196.8 | 68.6 | C-90 | 15.1 | 166.6 | 163.4 | | 878.4 | 5,355.7 | 0.02181 |
| 196.8 | 68.6 | C-95 | 15.1 | 166.6 | 163.4 | | 918.4 | 5,653.7 | 0.02181 |
| 196.8 | 68.6 | T-95 | 15.1 | 166.6 | 163.4 | | 918.4 | 5,653.7 | 0.02181 |
| 196.8 | 68.6 | P-110 | 15.1 | 166.6 | 163.4 | | 1,033.5 | 6,543.3 | 0.02181 |
| 196.8 | 68.6 | Q-125 | 15.1 | 166.6 | 163.4 | | 1,143.2 | 7,437.4 | 0.02181 |
| OD 8-5/8 in | | | | | | | | | |
| 219.1 | 35.72 | J-55 | 6.7 | 205.7 | 202.5 | | 94.5 | 1,694.8 | 0.03322 |
| 219.1 | 35.72 | K-55 | 6.7 | 205.7 | 202.5 | | 94.5 | 1,694.8 | 0.03322 |
| 219.1 | 35.72 | M-65 | 6.7 | 205.7 | 202.5 | | 98.6 | 2,006.1 | 0.03322 |
| 219.1 | 41.67 | H-40 | 7.7 | 203.6 | 200.5 | | 111 | 1,414.5 | 0.03257 |
| 219.1 | 47.62 | H-40 | 8.9 | 201.2 | 198 | | 151.7 | 1,628 | 0.03179 |
| 219.1 | 47.62 | J-55 | 8.9 | 201.2 | 198 | | 174.4 | 2,237.5 | 0.03179 |
| 219.1 | 47.62 | K-55 | 8.9 | 201.2 | 198 | | 174.4 | 2,237.5 | 0.03179 |
| 219.1 | 47.62 | M-65 | 8.9 | 201.2 | 198 | | 188.9 | 2,646.7 | 0.03179 |
| 219.1 | 53.57 | J-55 | 10.2 | 198.8 | 195.6 | | 237.9 | 2,526.6 | 0.03103 |
| 219.1 | 53.57 | K-55 | 10.2 | 198.8 | 195.6 | | 237.9 | 2,526.6 | 0.03103 |
| 219.1 | 53.57 | M-65 | 10.2 | 198.8 | 195.6 | | 259.2 | 2,989.2 | 0.03103 |
| 219.1 | 53.57 | L-80 | 10.2 | 198.8 | 195.6 | | 282.7 | 3,678.7 | 0.03103 |

Check every figure against your own pipe records before you pull.

# Casingjacks

Casingjacks LLC | sales@casingjack.com

## Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 1 of 2: size, collapse, body yield and capacity

| OD mm | Weight kg/m | Grade | Wall mm | ID mm | Drift mm | Drift source | Collapse bar | Body yield kN | Capacity m³/m |
|---|---|---|---|---|---|---|---|---|---|
| OD 8-5/8 in | | | | | | | | | |
| 219.1 | 53.57 | N-80 | 10.2 | 198.8 | 195.6 | | 282.7 | 3,678.7 | 0.03103 |
| 219.1 | 59.53 | M-65 | 11.4 | 196.2 | 193 | | 337.2 | 3,340.6 | 0.03024 |
| 219.1 | 59.53 | L-80 | 11.4 | 196.2 | 193 | | 380.6 | 4,114.6 | 0.03024 |
| 219.1 | 59.53 | N-80 | 11.4 | 196.2 | 193 | | 380.6 | 4,114.6 | 0.03024 |
| 219.1 | 59.53 | C-90 | 11.4 | 196.2 | 193 | | 404.7 | 4,626.2 | 0.03024 |
| 219.1 | 59.53 | C-95 | 11.4 | 196.2 | 193 | | 415.1 | 4,884.1 | 0.03024 |
| 219.1 | 59.53 | T-95 | 11.4 | 196.2 | 193 | | 415.1 | 4,884.1 | 0.03024 |
| 219.1 | 59.53 | P-110 | 11.4 | 196.2 | 193 | | 440.6 | 5,653.7 | 0.03024 |
| 219.1 | 65.48 | L-80 | 12.7 | 193.7 | 190.5 | | 479.2 | 4,541.6 | 0.02946 |
| 219.1 | 65.48 | N-80 | 12.7 | 193.7 | 190.5 | | 479.2 | 4,541.6 | 0.02946 |
| 219.1 | 65.48 | C-90 | 12.7 | 193.7 | 190.5 | | 516.4 | 5,111 | 0.02946 |
| 219.1 | 65.48 | C-95 | 12.7 | 193.7 | 190.5 | | 533.7 | 5,391.2 | 0.02946 |
| 219.1 | 65.48 | T-95 | 12.7 | 193.7 | 190.5 | | 533.7 | 5,391.2 | 0.02946 |
| 219.1 | 65.48 | P-110 | 12.7 | 193.7 | 190.5 | | 580.5 | 6,245.3 | 0.02946 |
| 219.1 | 65.48 | Q-125 | 12.7 | 193.7 | 190.5 | | 619.1 | 7,094.9 | 0.02946 |
| 219.1 | 72.92 | L-80 | 14.1 | 190.8 | 187.6 | | 591.6 | 5,022 | 0.02859 |
| 219.1 | 72.92 | N-80 | 14.1 | 190.8 | 187.6 | | 591.6 | 5,022 | 0.02859 |
| 219.1 | 72.92 | C-95 | 14.1 | 190.8 | 187.6 | | 669.5 | 5,965.1 | 0.02859 |
| 219.1 | 72.92 | T-95 | 14.1 | 190.8 | 187.6 | | 669.5 | 5,965.1 | 0.02859 |
| 219.1 | 72.92 | P-110 | 14.1 | 190.8 | 187.6 | | 740.5 | 6,908.1 | 0.02859 |
| 219.1 | 72.92 | Q-125 | 14.1 | 190.8 | 187.6 | | 803.2 | 7,851.1 | 0.02859 |
| OD 9-5/8 in | | | | | | | | | |
| 244.5 | 48.07 | H-40 | 7.9 | 228.6 | 224.7 | | 94.5 | 1,623.6 | 0.04105 |
| 244.5 | 53.57 | H-40 | 8.9 | 226.6 | 222.6 | | 118.6 | 1,823.8 | 0.04033 |
| 244.5 | 53.57 | J-55 | 8.9 | 226.6 | 222.6 | | 139.3 | 2,508.8 | 0.04033 |

Check every figure against your own pipe records before you pull.

# Casingjacks

Casingjacks LLC | sales@casingjack.com

## Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 1 of 2: size, collapse, body yield and capacity

| OD mm | Weight kg/m | Grade | Wall mm | ID mm | Drift mm | Drift source | Collapse bar | Body yield kN | Capacity m³/m |
|---|---|---|---|---|---|---|---|---|---|
| OD 9-5/8 in | | | | | | | | | |
| 244.5 | 53.57 | K-55 | 8.9 | 226.6 | 222.6 | | 139.3 | 2,508.8 | 0.04033 |
| 244.5 | 53.57 | M-65 | 8.9 | 226.6 | 222.6 | | 151 | 2,967 | 0.04033 |
| 244.5 | 59.53 | J-55 | 10 | 224.4 | 220.4 | | 177.2 | 2,802.4 | 0.03955 |
| 244.5 | 59.53 | K-55 | 10 | 224.4 | 220.4 | | 177.2 | 2,802.4 | 0.03955 |
| 244.5 | 59.53 | M-65 | 10 | 224.4 | 220.4 | | 191 | 3,313.9 | 0.03955 |
| 244.5 | 59.53 | L-80 | 10 | 224.4 | 220.4 | | 213 | 4,074.6 | 0.03955 |
| 244.5 | 59.53 | N-80 | 10 | 224.4 | 220.4 | | 213 | 4,074.6 | 0.03955 |
| 244.5 | 59.53 | C-90 | 10 | 224.4 | 220.4 | | 224.1 | 4,586.1 | 0.03955 |
| 244.5 | 59.53 | C-95 | 10 | 224.4 | 220.4 | | 228.9 | 4,839.7 | 0.03955 |
| 244.5 | 59.53 | T-95 | 10 | 224.4 | 220.4 | | 228.9 | 4,839.7 | 0.03955 |
| 244.5 | 64.74 | M-65 | 11 | 222.4 | 218.4 | | 242.7 | 3,629.7 | 0.03884 |
| 244.5 | 64.74 | L-80 | 11 | 222.4 | 218.4 | | 262.7 | 4,470.5 | 0.03884 |
| 244.5 | 64.74 | N-80 | 11 | 222.4 | 218.4 | | 262.7 | 4,470.5 | 0.03884 |
| 244.5 | 64.74 | C-90 | 11 | 222.4 | 218.4 | | 276.5 | 5,026.5 | 0.03884 |
| 244.5 | 64.74 | C-95 | 11 | 222.4 | 218.4 | | 284.1 | 5,306.7 | 0.03884 |
| 244.5 | 64.74 | T-95 | 11 | 222.4 | 218.4 | | 284.1 | 5,306.7 | 0.03884 |
| 244.5 | 64.74 | P-110 | 11 | 222.4 | 218.4 | | 304.7 | 6,143 | 0.03884 |
| 244.5 | 64.74 | Q-125 | 11 | 222.4 | 218.4 | | 318.5 | 6,983.7 | 0.03884 |
| 244.5 | 69.94 | L-80 | 12 | 220.5 | 216.5 | | 328.2 | 4,830.8 | 0.03819 |
| 244.5 | 69.94 | N-80 | 12 | 220.5 | 216.5 | | 328.2 | 4,830.8 | 0.03819 |
| 244.5 | 69.94 | C-90 | 12 | 220.5 | 216.5 | | 344.7 | 5,431.3 | 0.03819 |
| 244.5 | 69.94 | C-95 | 12 | 220.5 | 216.5 | | 350.9 | 5,733.8 | 0.03819 |
| 244.5 | 69.94 | T-95 | 12 | 220.5 | 216.5 | | 350.9 | 5,733.8 | 0.03819 |
| 244.5 | 69.94 | P-110 | 12 | 220.5 | 216.5 | | 365.4 | 6,641.2 | 0.03819 |
| 244.5 | 69.94 | Q-125 | 12 | 220.5 | 216.5 | | 388.9 | 7,548.6 | 0.03819 |

Check every figure against your own pipe records before you pull.

# Casingjacks

Casingjacks LLC | sales@casingjack.com

## Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 1 of 2: size, collapse, body yield and capacity

| OD mm | Weight kg/m | Grade | Wall mm | ID mm | Drift mm | Drift source | Collapse bar | Body yield kN | Capacity m³/m |
|---|---|---|---|---|---|---|---|---|---|
| OD 9-5/8 in | | | | | | | | | |
| 244.5 | 79.62 | L-80 | 13.8 | 216.8 | 212.8 | | 456.4 | 5,533.6 | 0.03691 |
| 244.5 | 79.62 | N-80 | 13.8 | 216.8 | 212.8 | | 456.4 | 5,533.6 | 0.03691 |
| 244.5 | 79.62 | C-90 | 13.8 | 216.8 | 212.8 | | 490.9 | 6,223.1 | 0.03691 |
| 244.5 | 79.62 | C-95 | 13.8 | 216.8 | 212.8 | | 506.1 | 6,570 | 0.03691 |
| 244.5 | 79.62 | T-95 | 13.8 | 216.8 | 212.8 | | 506.1 | 6,570 | 0.03691 |
| 244.5 | 79.62 | P-110 | 13.8 | 216.8 | 212.8 | | 548.1 | 7,606.5 | 0.03691 |
| 244.5 | 79.62 | Q-125 | 13.8 | 216.8 | 212.8 | | 581.9 | 8,642.9 | 0.03691 |
| 244.5 | 86.91 | L-80 | 15.1 | 214.2 | 210.3 | | 544 | 6,005.1 | 0.03605 |
| 244.5 | 86.91 | N-80 | 15.1 | 214.2 | 210.3 | | 544 | 6,005.1 | 0.03605 |
| 244.5 | 86.91 | C-90 | 15.1 | 214.2 | 210.3 | | 590.2 | 6,756.8 | 0.03605 |
| 244.5 | 86.91 | C-95 | 15.1 | 214.2 | 210.3 | | 612.3 | 7,134.9 | 0.03605 |
| 244.5 | 86.91 | T-95 | 15.1 | 214.2 | 210.3 | | 612.3 | 7,134.9 | 0.03605 |
| 244.5 | 86.91 | P-110 | 15.1 | 214.2 | 210.3 | | 672.9 | 8,260.3 | 0.03605 |
| 244.5 | 86.91 | Q-125 | 15.1 | 214.2 | 210.3 | | 726 | 9,385.7 | 0.03605 |
| 244.5 | 88.4 | C-90 | 15.5 | 213.5 | 209.6 | | 619.1 | 6,908.1 | 0.03581 |
| 244.5 | 88.4 | T-95 | 15.5 | 213.5 | 209.6 | | 642.6 | 7,268.4 | 0.03581 |
| 244.5 | 96.58 | C-90 | 17.1 | 210.3 | 206.4 | | 744.6 | 7,566.4 | 0.03475 |
| 244.5 | 96.58 | T-95 | 17.1 | 210.3 | 206.4 | | 776.3 | 7,989 | 0.03475 |
| 244.5 | 104.62 | C-90 | 18.6 | 207.2 | 203.2 | | 869.4 | 8,207 | 0.03372 |
| 244.5 | 104.62 | T-95 | 18.6 | 207.2 | 203.2 | | 908.7 | 8,665.1 | 0.03372 |
| 244.5 | 112.51 | C-90 | 20.2 | 204 | 200 | | 942.5 | 8,847.5 | 0.03268 |
| 244.5 | 112.51 | T-95 | 20.2 | 204 | 200 | | 994.9 | 9,341.3 | 0.03268 |
| OD 9-3/4 in | | | | | | | | | |
| 247.6 | 88.1 | P-110 | 15.1 | 217.4 | 215.9 | | 654.3 | 8,371.6 | 0.03713 |
| 247.6 | 88.1 | Q-125 | 15.1 | 217.4 | 215.9 | | 704 | 9,514.7 | 0.03713 |

Check every figure against your own pipe records before you pull.

# Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 1 of 2: size, collapse, body yield and capacity

| OD mm | Weight kg/m | Grade | Wall mm | ID mm | Drift mm | Drift source | Collapse bar | Body yield kN | Capacity m³/m |
|---|---|---|---|---|---|---|---|---|---|
| OD 9-7/8 in | | | | | | | | | |
| 250.8 | 93.46 | P-110 | 15.9 | 219.1 | 215.9 | | 708.8 | 8,887.5 | 0.03769 |
| 250.8 | 93.46 | Q-125 | 15.9 | 219.1 | 215.9 | | 768.1 | 10,097.5 | 0.03769 |
| OD 10-3/4 in | | | | | | | | | |
| 273.1 | 48.74 | H-40 | 7.1 | 258.9 | 254.9 | | 57.9 | 1,632.5 | 0.05264 |
| 273.1 | 60.27 | H-40 | 8.9 | 255.3 | 251.3 | | 95.8 | 2,032.8 | 0.05118 |
| 273.1 | 60.27 | J-55 | 8.9 | 255.3 | 251.3 | | 108.9 | 2,797.9 | 0.05118 |
| 273.1 | 60.27 | K-55 | 8.9 | 255.3 | 251.3 | | 108.9 | 2,797.9 | 0.05118 |
| 273.1 | 60.27 | M-65 | 8.9 | 255.3 | 251.3 | | 115.8 | 3,305 | 0.05118 |
| 273.1 | 60.27 | N-80 | 8.9 | 255.3 | 251.3 | | 119.3 | 4,070.1 | 0.05118 |
| 273.1 | 67.71 | J-55 | 10.2 | 252.7 | 248.8 | | 144.1 | 3,180.5 | 0.05017 |
| 273.1 | 67.71 | M-65 | 10.2 | 252.7 | 248.8 | | 157.2 | 3,758.7 | 0.05017 |
| 273.1 | 67.71 | N-80 | 10.2 | 252.7 | 248.8 | | 170.3 | 4,626.2 | 0.05017 |
| 273.1 | 75.9 | J-55 | 11.4 | 250.2 | 246.2 | | 186.2 | 3,563 | 0.04916 |
| 273.1 | 75.9 | K-55 | 11.4 | 250.2 | 246.2 | | 186.2 | 3,563 | 0.04916 |
| 273.1 | 75.9 | M-65 | 11.4 | 250.2 | 246.2 | | 197.9 | 4,208 | 0.04916 |
| 273.1 | 75.9 | L-80 | 11.4 | 250.2 | 246.2 | | 222 | 5,182.2 | 0.04916 |
| 273.1 | 75.9 | N-80 | 11.4 | 250.2 | 246.2 | | 222 | 5,182.2 | 0.04916 |
| 273.1 | 75.9 | C-90 | 11.4 | 250.2 | 246.2 | | 234.4 | 5,831.6 | 0.04916 |
| 273.1 | 75.9 | C-95 | 11.4 | 250.2 | 246.2 | | 239.9 | 6,151.9 | 0.04916 |
| 273.1 | 75.9 | T-95 | 11.4 | 250.2 | 246.2 | | 239.9 | 6,151.9 | 0.04916 |
| 273.1 | 75.9 | P-110 | 11.4 | 250.2 | 246.2 | | 252.3 | 7,126.1 | 0.04916 |
| 273.1 | 75.9 | Q-125 | 11.4 | 250.2 | 246.2 | | 257.9 | 8,095.8 | 0.04916 |
| 273.1 | 82.59 | L-80 | 12.6 | 247.9 | 243.9 | | 277.2 | 5,675.9 | 0.04827 |
| 273.1 | 82.59 | N-80 | 12.6 | 247.9 | 243.9 | | 277.2 | 5,675.9 | 0.04827 |
| 273.1 | 82.59 | C-90 | 12.6 | 247.9 | 243.9 | | 286.8 | 6,383.2 | 0.04827 |

Check every figure against your own pipe records before you pull.

# Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 1 of 2: size, collapse, body yield and capacity

| OD mm | Weight kg/m | Grade | Wall mm | ID mm | Drift mm | Drift source | Collapse bar | Body yield kN | Capacity m³/m |
|---|---|---|---|---|---|---|---|---|---|
| OD 10-3/4 in | | | | | | | | | |
| 273.1 | 82.59 | C-95 | 12.6 | 247.9 | 243.9 | | 295.8 | 6,739.1 | 0.04827 |
| 273.1 | 82.59 | T-95 | 12.6 | 247.9 | 243.9 | | 295.8 | 6,739.1 | 0.04827 |
| 273.1 | 82.59 | P-110 | 12.6 | 247.9 | 243.9 | | 317.8 | 7,802.2 | 0.04827 |
| 273.1 | 82.59 | Q-125 | 12.6 | 247.9 | 243.9 | | 334.4 | 8,865.3 | 0.04827 |
| 273.1 | 90.33 | L-80 | 13.8 | 245.4 | 241.4 | | 355.8 | 6,218.6 | 0.04728 |
| 273.1 | 90.33 | N-80 | 13.8 | 245.4 | 241.4 | | 355.8 | 6,218.6 | 0.04728 |
| 273.1 | 90.33 | C-90 | 13.8 | 245.4 | 241.4 | | 376.5 | 6,997.1 | 0.04728 |
| 273.1 | 90.33 | C-95 | 13.8 | 245.4 | 241.4 | | 385.4 | 7,384 | 0.04728 |
| 273.1 | 90.33 | T-95 | 13.8 | 245.4 | 241.4 | | 385.4 | 7,384 | 0.04728 |
| 273.1 | 90.33 | P-110 | 13.8 | 245.4 | 241.4 | | 405.4 | 8,549.5 | 0.04728 |
| 273.1 | 90.33 | Q-125 | 13.8 | 245.4 | 241.4 | | 418.5 | 9,714.9 | 0.04728 |
| 273.1 | 97.77 | L-80 | 15.1 | 242.8 | 238.9 | | 434.4 | 6,756.8 | 0.04631 |
| 273.1 | 97.77 | N-80 | 15.1 | 242.8 | 238.9 | | 434.4 | 6,756.8 | 0.04631 |
| 273.1 | 97.77 | C-90 | 15.1 | 242.8 | 238.9 | | 466.1 | 7,597.6 | 0.04631 |
| 273.1 | 97.77 | T-95 | 15.1 | 242.8 | 238.9 | | 479.9 | 8,020.1 | 0.04631 |
| 273.1 | 97.77 | P-110 | 15.1 | 242.8 | 238.9 | | 517.1 | 9,287.9 | 0.04631 |
| 273.1 | 97.77 | Q-125 | 15.1 | 242.8 | 238.9 | | 546.1 | 10,555.6 | 0.04631 |
| 273.1 | 105.81 | P-110 | 16.5 | 240 | 236.1 | | 641.2 | 10,093 | 0.04525 |
| 273.1 | 105.81 | Q-125 | 16.5 | 240 | 236.1 | | 688.8 | 11,467.5 | 0.04525 |
| 273.1 | 108.93 | C-90 | 17.1 | 238.9 | 234.9 | | 604 | 8,518.3 | 0.04483 |
| 273.1 | 108.93 | T-95 | 17.1 | 238.9 | 234.9 | | 626.7 | 8,989.9 | 0.04483 |
| 273.1 | 117.86 | C-90 | 18.6 | 235.8 | 231.8 | | 715 | 9,247.9 | 0.04366 |
| 273.1 | 117.86 | T-95 | 18.6 | 235.8 | 231.8 | | 744.6 | 9,759.4 | 0.04366 |
| 273.1 | 126.94 | C-90 | 20.2 | 232.6 | 228.6 | | 828.1 | 9,977.4 | 0.04248 |
| 273.1 | 126.94 | T-95 | 20.2 | 232.6 | 228.6 | | 864.6 | 10,528.9 | 0.04248 |

Check every figure against your own pipe records before you pull.

# Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 1 of 2: size, collapse, body yield and capacity

| OD mm | Weight kg/m | Grade | Wall mm | ID mm | Drift mm | Drift source | Collapse bar | Body yield kN | Capacity m³/m |
|---|---|---|---|---|---|---|---|---|---|
| OD 11-3/4 in | | | | | | | | | |
| 298.4 | 62.5 | H-40 | 8.5 | 281.5 | 277.6 | | 71.7 | 2,126.2 | 0.06225 |
| 298.4 | 69.94 | J-55 | 9.5 | 279.4 | 275.4 | | 104.1 | 3,278.3 | 0.06131 |
| 298.4 | 69.94 | K-55 | 9.5 | 279.4 | 275.4 | | 104.1 | 3,278.3 | 0.06131 |
| 298.4 | 69.94 | M-65 | 9.5 | 279.4 | 275.4 | | 109.6 | 3,874.4 | 0.06131 |
| 298.4 | 80.36 | J-55 | 11 | 276.4 | 272.4 | | 142.7 | 3,781 | 0.05998 |
| 298.4 | 80.36 | K-55 | 11 | 276.4 | 272.4 | | 142.7 | 3,781 | 0.05998 |
| 298.4 | 80.36 | M-65 | 11 | 276.4 | 272.4 | | 155.1 | 4,470.5 | 0.05998 |
| 298.4 | 89.29 | J-55 | 12.4 | 273.6 | 269.6 | | 183.4 | 4,234.7 | 0.0588 |
| 298.4 | 89.29 | K-55 | 12.4 | 273.6 | 269.6 | | 183.4 | 4,234.7 | 0.0588 |
| 298.4 | 89.29 | M-65 | 12.4 | 273.6 | 269.6 | | 195.8 | 5,004.2 | 0.0588 |
| 298.4 | 89.29 | L-80 | 12.4 | 273.6 | 269.6 | | 219.3 | 6,156.3 | 0.0588 |
| 298.4 | 89.29 | N-80 | 12.4 | 273.6 | 269.6 | | 219.3 | 6,156.3 | 0.0588 |
| 298.4 | 89.29 | C-90 | 12.4 | 273.6 | 269.6 | | 231.7 | 6,925.9 | 0.0588 |
| 298.4 | 89.29 | C-95 | 12.4 | 273.6 | 269.6 | | 237.2 | 7,312.9 | 0.0588 |
| 298.4 | 89.29 | T-95 | 12.4 | 273.6 | 269.6 | | 237.2 | 7,312.9 | 0.0588 |
| 298.4 | 89.29 | P-110 | 12.4 | 273.6 | 269.6 | | 248.9 | 8,465 | 0.0588 |
| 298.4 | 89.29 | Q-125 | 12.4 | 273.6 | 269.6 | | 253.7 | 9,621.5 | 0.0588 |
| 298.4 | 96.73 | M-65 | 13.6 | 271.3 | 267.4 | | 246.8 | 5,440.2 | 0.05782 |
| 298.4 | 96.73 | L-80 | 13.6 | 271.3 | 267.4 | | 266.8 | 6,694.6 | 0.05782 |
| 298.4 | 96.73 | N-80 | 13.6 | 271.3 | 267.4 | | 266.8 | 6,694.6 | 0.05782 |
| 298.4 | 96.73 | P-110 | 13.6 | 271.3 | 267.4 | | 308.9 | 9,207.8 | 0.05782 |
| 298.4 | 96.73 | Q-125 | 13.6 | 271.3 | 267.4 | | 323.4 | 10,462.2 | 0.05782 |
| 298.4 | 105.66 | Q-125 | 14.8 | 268.9 | 264.9 | | 397.1 | 11,351.9 | 0.05678 |
| OD 11-7/8 in | | | | | | | | | |
| 301.6 | 106.85 | P-110 | 14.8 | 272.1 | 269.9 | | 364.7 | 10,101.9 | 0.05813 |

Check every figure against your own pipe records before you pull.

# Casingjacks

Casingjacks LLC | sales@casingjack.com

## Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 1 of 2: size, collapse, body yield and capacity

| OD mm | Weight kg/m | Grade | Wall mm | ID mm | Drift mm | Drift source | Collapse bar | Body yield kN | Capacity m³/m |
|---|---|---|---|---|---|---|---|---|---|
| OD 11-7/8 in | | | | | | | | | |
| 301.6 | 106.85 | Q-125 | 14.8 | 272.1 | 269.9 | | 388.2 | 11,480.9 | 0.05813 |
| OD 13-3/8 in | | | | | | | | | |
| 339.7 | 71.43 | H-40 | 8.4 | 323 | 319 | | 51 | 2,406.5 | 0.08192 |
| 339.7 | 81.1 | J-55 | 9.7 | 320.4 | 316.5 | | 77.9 | 3,794.3 | 0.08064 |
| 339.7 | 81.1 | K-55 | 9.7 | 320.4 | 316.5 | | 77.9 | 3,794.3 | 0.08064 |
| 339.7 | 81.1 | M-65 | 9.7 | 320.4 | 316.5 | | 78.6 | 4,483.8 | 0.08064 |
| 339.7 | 90.78 | J-55 | 10.9 | 317.9 | 313.9 | | 106.2 | 4,279.2 | 0.07936 |
| 339.7 | 90.78 | K-55 | 10.9 | 317.9 | 313.9 | | 106.2 | 4,279.2 | 0.07936 |
| 339.7 | 90.78 | M-65 | 10.9 | 317.9 | 313.9 | | 111.7 | 5,057.6 | 0.07936 |
| 339.7 | 101.2 | J-55 | 12.2 | 315.3 | 311.4 | | 134.4 | 4,755.1 | 0.0781 |
| 339.7 | 101.2 | K-55 | 12.2 | 315.3 | 311.4 | | 134.4 | 4,755.1 | 0.0781 |
| 339.7 | 101.2 | M-65 | 12.2 | 315.3 | 311.4 | | 145.5 | 5,622.6 | 0.0781 |
| 339.7 | 101.2 | L-80 | 12.2 | 315.3 | 311.4 | | 155.8 | 6,921.4 | 0.0781 |
| 339.7 | 101.2 | N-80 | 12.2 | 315.3 | 311.4 | | 155.8 | 6,921.4 | 0.0781 |
| 339.7 | 101.2 | C-90 | 12.2 | 315.3 | 311.4 | | 160 | 7,784.4 | 0.0781 |
| 339.7 | 101.2 | C-95 | 12.2 | 315.3 | 311.4 | | 160.6 | 8,215.9 | 0.0781 |
| 339.7 | 101.2 | T-95 | 12.2 | 315.3 | 311.4 | | 160.6 | 8,215.9 | 0.0781 |
| 339.7 | 101.2 | P-110 | 12.2 | 315.3 | 311.4 | | 161.3 | 9,514.7 | 0.0781 |
| 339.7 | 107.15 | M-65 | 13.1 | 313.6 | 309.7 | | 167.5 | 6,005.1 | 0.07725 |
| 339.7 | 107.15 | L-80 | 13.1 | 313.6 | 309.7 | | 184.1 | 7,388.5 | 0.07725 |
| 339.7 | 107.15 | N-80 | 13.1 | 313.6 | 309.7 | | 184.1 | 7,388.5 | 0.07725 |
| 339.7 | 107.15 | C-90 | 13.1 | 313.6 | 309.7 | | 191.7 | 8,313.7 | 0.07725 |
| 339.7 | 107.15 | C-95 | 13.1 | 313.6 | 309.7 | | 194.4 | 8,776.3 | 0.07725 |
| 339.7 | 107.15 | T-95 | 13.1 | 313.6 | 309.7 | | 194.4 | 8,776.3 | 0.07725 |
| 339.7 | 107.15 | P-110 | 13.1 | 313.6 | 309.7 | | 199.3 | 10,159.7 | 0.07725 |

Check every figure against your own pipe records before you pull.

# Casingjacks

Casingjacks LLC | sales@casingjack.com

## Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 1 of 2: size, collapse, body yield and capacity

| OD mm | Weight kg/m | Grade | Wall mm | ID mm | Drift mm | Drift source | Collapse bar | Body yield kN | Capacity m³/m |
|---|---|---|---|---|---|---|---|---|---|
| OD 13-3/8 in | | | | | | | | | |
| 339.7 | 107.15 | Q-125 | 13.1 | 313.6 | 309.7 | | 198.6 | 11,547.6 | 0.07725 |
| 339.7 | 120.09 | P-110 | 14.7 | 310.3 | 306.3 | | 275.8 | 11,409.7 | 0.0756 |
| 339.7 | 120.09 | Q-125 | 14.7 | 310.3 | 306.3 | | 285.4 | 12,962.1 | 0.0756 |
| 339.7 | 127.98 | P-110 | 15.9 | 308 | 304 | | 329.6 | 12,250.4 | 0.07449 |
| 339.7 | 127.98 | Q-125 | 15.9 | 308 | 304 | | 346.8 | 13,918.5 | 0.07449 |
| OD 13-1/2 in | | | | | | | | | |
| 342.9 | 121.14 | P-110 | 14.7 | 313.4 | 311.1 | | 269.6 | 11,520.9 | 0.07716 |
| 342.9 | 121.14 | Q-125 | 14.7 | 313.4 | 311.1 | | 277.9 | 13,091.1 | 0.07716 |
| OD 13-5/8 in | | | | | | | | | |
| 346.1 | 131.26 | P-110 | 15.9 | 314.3 | 311.1 | | 315.1 | 12,490.6 | 0.0776 |
| 346.1 | 131.26 | Q-125 | 15.9 | 314.3 | 311.1 | | 330.9 | 14,194.3 | 0.0776 |
| OD 16 in | | | | | | | | | |
| 406.4 | 96.73 | H-40 | 9.5 | 387.3 | 382.6 | | 43.4 | 3,273.9 | 0.11784 |
| 406.4 | 111.61 | J-55 | 11.1 | 384.1 | 379.4 | | 70.3 | 5,240 | 0.1159 |
| 406.4 | 111.61 | K-55 | 11.1 | 384.1 | 379.4 | | 70.3 | 5,240 | 0.1159 |
| 406.4 | 111.61 | M-65 | 11.1 | 384.1 | 379.4 | | 70.3 | 6,191.9 | 0.1159 |
| 406.4 | 125.01 | J-55 | 12.6 | 381.3 | 376.5 | | 97.2 | 5,898.3 | 0.11416 |
| 406.4 | 125.01 | K-55 | 12.6 | 381.3 | 376.5 | | 97.2 | 5,898.3 | 0.11416 |
| 406.4 | 125.01 | M-65 | 12.6 | 381.3 | 376.5 | | 101.4 | 6,970.4 | 0.11416 |
| 406.4 | 125.01 | N-80 | 12.6 | 381.3 | 376.5 | | 102 | 8,580.6 | 0.11416 |
| 406.4 | 125.01 | P-110 | 12.6 | 381.3 | 376.5 | | 102 | 11,796.7 | 0.11416 |
| 406.4 | 125.01 | Q-125 | 12.6 | 381.3 | 376.5 | | 102 | 13,406.9 | 0.11416 |
| 406.4 | 141.38 | N-80 | 14.4 | 377.6 | 372.9 | CALC | 150.3 | 9,768.3 | 0.11201 |
| 406.4 | 141.38 | P-110 | 14.4 | 377.6 | 372.9 | CALC | 153.8 | 13,429.2 | 0.11201 |
| 406.4 | 141.38 | Q-125 | 14.4 | 377.6 | 372.9 | CALC | 153.8 | 15,261.8 | 0.11201 |

Check every figure against your own pipe records before you pull.

# Casingjacks

Casingjacks LLC | sales@casingjack.com

## Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 1 of 2: size, collapse, body yield and capacity

| OD mm | Weight kg/m | Grade | Wall mm | ID mm | Drift mm | Drift source | Collapse bar | Body yield kN | Capacity m³/m |
|---|---|---|---|---|---|---|---|---|---|
| OD 16 in | | | | | | | | | |
| 406.4 | 144.35 | N-80 | 14.6 | 377.2 | 372.4 | CALC | 156.5 | 9,919.5 | 0.11174 |
| 406.4 | 144.35 | P-110 | 14.6 | 377.2 | 372.4 | CALC | 161.3 | 13,642.7 | 0.11174 |
| 406.4 | 144.35 | Q-125 | 14.6 | 377.2 | 372.4 | CALC | 161.3 | 15,502.1 | 0.11174 |
| 406.4 | 162.21 | J-55 | 16.7 | 373.1 | 368.3 | | 176.5 | 7,735.5 | 0.10932 |
| 406.4 | 162.21 | K-55 | 16.7 | 373.1 | 368.3 | | 176.5 | 7,735.5 | 0.10932 |
| 406.4 | 162.21 | N-80 | 16.7 | 373.1 | 368.3 | | 212.4 | 11,254 | 0.10932 |
| 406.4 | 175.6 | J-55 | 18.2 | 370.1 | 365.3 | | 218.6 | 8,402.7 | 0.10757 |
| 406.4 | 175.6 | K-55 | 18.2 | 370.1 | 365.3 | | 218.6 | 8,402.7 | 0.10757 |
| 406.4 | 175.6 | N-80 | 18.2 | 370.1 | 365.3 | | 253.7 | 12,219.3 | 0.10757 |
| OD 18-5/8 in | | | | | | | | | |
| 473.1 | 130.21 | H-40 | 11 | 451 | 446.2 | | 43.4 | 4,426 | 0.15974 |
| 473.1 | 130.21 | J-55 | 11 | 451 | 446.2 | | 43.4 | 6,085.2 | 0.15974 |
| 473.1 | 130.21 | K-55 | 11 | 451 | 446.2 | | 43.4 | 6,085.2 | 0.15974 |
| 473.1 | 130.21 | N-80 | 11 | 451 | 446.2 | | 43.4 | 8,852 | 0.15974 |
| 473.1 | 140.63 | H-40 | 11.9 | 449.3 | 444.5 | | 53.8 | 4,750.7 | 0.15855 |
| 473.1 | 140.63 | J-55 | 11.9 | 449.3 | 444.5 | | 53.8 | 6,534.4 | 0.15855 |
| 473.1 | 140.63 | K-55 | 11.9 | 449.3 | 444.5 | | 53.8 | 6,534.4 | 0.15855 |
| 473.1 | 140.63 | N-80 | 11.9 | 449.3 | 444.5 | | 53.8 | 9,505.8 | 0.15855 |
| 473.1 | 157.75 | J-55 | 13.5 | 446.1 | 441.3 | | 78.6 | 7,388.5 | 0.1563 |
| 473.1 | 157.75 | K-55 | 13.5 | 446.1 | 441.3 | | 78.6 | 7,388.5 | 0.1563 |
| 473.1 | 157.75 | N-80 | 13.5 | 446.1 | 441.3 | | 79.3 | 10,746.9 | 0.1563 |
| 473.1 | 174.86 | J-55 | 15.1 | 443 | 438.2 | | 104.1 | 8,224.8 | 0.1541 |
| 473.1 | 174.86 | K-55 | 15.1 | 443 | 438.2 | | 104.1 | 8,224.8 | 0.1541 |
| 473.1 | 174.86 | N-80 | 15.1 | 443 | 438.2 | | 111.7 | 11,961.3 | 0.1541 |

Check every figure against your own pipe records before you pull.

# Casingjacks

Casingjacks LLC | sales@casingjack.com

## Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 1 of 2: size, collapse, body yield and capacity

| OD mm | Weight kg/m | Grade | Wall mm | ID mm | Drift mm | Drift source | Collapse bar | Body yield kN | Capacity m³/m |
|---|---|---|---|---|---|---|---|---|---|
| OD 20 in | | | | | | | | | |
| 508 | 139.89 | H-40 | 11.1 | 485.7 | 481 | | 35.9 | 4,790.7 | 0.18532 |
| 508 | 139.89 | J-55 | 11.1 | 485.7 | 481 | | 35.9 | 6,583.4 | 0.18532 |
| 508 | 139.89 | K-55 | 11.1 | 485.7 | 481 | | 35.9 | 6,583.4 | 0.18532 |
| 508 | 158.49 | J-55 | 12.7 | 482.6 | 477.8 | | 53.1 | 7,495.3 | 0.18292 |
| 508 | 158.49 | K-55 | 12.7 | 482.6 | 477.8 | | 53.1 | 7,495.3 | 0.18292 |
| 508 | 158.49 | N-80 | 12.7 | 482.6 | 477.8 | | 53.1 | 10,898.1 | 0.18292 |
| 508 | 197.93 | K-55 | 16.1 | 475.7 | 471 | | 103.4 | 9,452.5 | 0.17776 |
| 508 | 197.93 | L-80 | 16.1 | 475.7 | 471 | | 110.3 | 13,749.5 | 0.17776 |
| 508 | 197.93 | N-80 | 16.1 | 475.7 | 471 | | 110.3 | 13,749.5 | 0.17776 |
| 508 | 251.5 | K-55 | 20.6 | 466.8 | 462 | | 172.4 | 11,974.6 | 0.17111 |
| 508 | 251.5 | L-80 | 20.6 | 466.8 | 462 | | 208.2 | 17,419.2 | 0.17111 |
| 508 | 251.5 | N-80 | 20.6 | 466.8 | 462 | | 208.2 | 17,419.2 | 0.17111 |

# Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 2 of 2: internal yield and joint strength

| OD mm | Weight kg/m | Grade | Internal yield PE bar | Internal yield STC bar | Internal yield LTC bar | Internal yield BTC bar | Joint STC kN | Joint LTC kN | Joint BTC kN |
|---|---|---|---|---|---|---|---|---|---|
| OD 4-1/2 in | | | | | | | | | |
| 114.3 | 14.14 | J-55 | 302 | 302 | Not recorded | Not recorded | 449.3 | Not recorded | Not recorded |
| 114.3 | 14.14 | K-55 | 302 | 302 | Not recorded | Not recorded | 498.2 | Not recorded | Not recorded |
| 114.3 | 14.14 | M-65 | 357.1 | 357.1 | Not recorded | Not recorded | 600.5 | Not recorded | Not recorded |
| 114.3 | 15.63 | J-55 | 330.3 | 330.3 | Not recorded | 330.3 | 587.2 | Not recorded | 903 |
| 114.3 | 15.63 | K-55 | 330.3 | 330.3 | Not recorded | 330.3 | 649.4 | Not recorded | 1,107.6 |
| 114.3 | 15.63 | M-65 | 390.2 | 390.2 | Not recorded | 390.2 | 685 | Not recorded | 1,027.5 |
| 114.3 | 17.26 | J-55 | 368.9 | 368.9 | 368.9 | 368.9 | 685 | 720.6 | 1,000.8 |
| 114.3 | 17.26 | K-55 | 368.9 | 368.9 | 368.9 | 368.9 | 756.2 | 800.7 | 1,232.2 |
| 114.3 | 17.26 | M-65 | 435.7 | 435.7 | 435.7 | 435.7 | 796.2 | 836.3 | 1,138.7 |
| 114.3 | 17.26 | L-80 | 536.4 | Not recorded | 536.4 | 536.4 | Not recorded | 943 | 1,294.4 |
| 114.3 | 17.26 | N-80 | 536.4 | Not recorded | 536.4 | 536.4 | Not recorded | 992 | 1,352.3 |
| 114.3 | 17.26 | C-90 | 603.3 | Not recorded | 603.3 | 603.3 | Not recorded | 992 | 1,374.5 |
| 114.3 | 17.26 | C-95 | 637.1 | Not recorded | 637.1 | 637.1 | Not recorded | 1,040.9 | 1,445.7 |
| 114.3 | 17.26 | T-95 | 637.1 | Not recorded | 637.1 | 637.1 | Not recorded | 1,040.9 | 1,445.7 |
| 114.3 | 17.26 | P-110 | 737 | Not recorded | 737 | 737 | Not recorded | 1,241.1 | 1,712.6 |
| 114.3 | 20.09 | M-65 | 505.4 | Not recorded | 505.4 | 505.4 | Not recorded | 1,014.2 | 1,312.2 |
| 114.3 | 20.09 | L-80 | 621.9 | Not recorded | 621.9 | 621.9 | Not recorded | 1,143.2 | 1,485.7 |
| 114.3 | 20.09 | N-80 | 621.9 | Not recorded | 621.9 | 621.9 | Not recorded | 1,201 | 1,552.4 |
| 114.3 | 20.09 | C-90 | 699.8 | Not recorded | 699.8 | 699.8 | Not recorded | 1,201 | 1,579.1 |
| 114.3 | 20.09 | C-95 | 738.4 | Not recorded | 738.4 | 738.4 | Not recorded | 1,263.3 | 1,663.6 |
| 114.3 | 20.09 | T-95 | 738.4 | Not recorded | 738.4 | 738.4 | Not recorded | 1,263.3 | 1,663.6 |
| 114.3 | 20.09 | P-110 | 855.6 | Not recorded | 855.6 | 855.6 | Not recorded | 1,503.5 | 1,970.6 |
| 114.3 | 22.47 | L-80 | 722.6 | Not recorded | 722.6 | 722.6 | Not recorded | 1,370.1 | 1,708.1 |
| 114.3 | 22.47 | P-110 | 994.2 | Not recorded | 994.2 | 928 | Not recorded | 1,806 | 2,264.1 |
| 114.3 | 22.47 | Q-125 | 1,129.4 | Not recorded | 1,129.4 | 1,054.9 | Not recorded | 1,948.3 | 2,464.3 |

Check every figure against your own pipe records before you pull.

## Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 2 of 2: internal yield and joint strength

| OD mm | Weight kg/m | Grade | Internal yield PE bar | Internal yield STC bar | Internal yield LTC bar | Internal yield BTC bar | Joint STC kN | Joint LTC kN | Joint BTC kN |
|---|---|---|---|---|---|---|---|---|---|
| OD 5 in | | | | | | | | | |
| 127 | 17.11 | J-55 | 292.3 | 292.3 | Not recorded | Not recorded | 591.6 | Not recorded | Not recorded |
| 127 | 17.11 | K-55 | 292.3 | 292.3 | Not recorded | Not recorded | 653.9 | Not recorded | Not recorded |
| 127 | 17.11 | M-65 | 345.4 | 345.4 | Not recorded | Not recorded | 720.6 | Not recorded | Not recorded |
| 127 | 19.35 | J-55 | 335.8 | 335.8 | 335.8 | 335.8 | 751.7 | 809.6 | 1,121 |
| 127 | 19.35 | K-55 | 335.8 | 335.8 | 335.8 | 335.8 | 827.4 | 894.1 | 1,374.5 |
| 127 | 19.35 | M-65 | 397.1 | 397.1 | 397.1 | 397.1 | 871.9 | 943 | 1,281.1 |
| 127 | 22.32 | J-55 | 393 | 393 | 393 | 393 | 920.8 | 992 | 1,303.3 |
| 127 | 22.32 | K-55 | 393 | 393 | 393 | 393 | 1,014.2 | 1,094.3 | 1,596.9 |
| 127 | 22.32 | M-65 | 464 | 464 | 464 | 464 | 1,067.6 | 1,152.1 | 1,485.7 |
| 127 | 22.32 | L-80 | 571.6 | Not recorded | 571.6 | 571.6 | Not recorded | 1,312.2 | 1,685.9 |
| 127 | 22.32 | N-80 | 571.6 | Not recorded | 571.6 | 571.6 | Not recorded | 1,383.4 | 1,761.5 |
| 127 | 22.32 | C-90 | 642.6 | Not recorded | 642.6 | 642.6 | Not recorded | 1,383.4 | 1,797.1 |
| 127 | 22.32 | C-95 | 678.4 | Not recorded | 678.4 | 678.4 | Not recorded | 1,450.1 | 1,886 |
| 127 | 22.32 | T-95 | 678.4 | Not recorded | 678.4 | 678.4 | Not recorded | 1,450.1 | 1,886 |
| 127 | 22.32 | P-110 | 786 | Not recorded | 786 | 786 | Not recorded | 1,725.9 | 2,237.5 |
| 127 | 26.79 | M-65 | 568.1 | Not recorded | 568.1 | 568.1 | Not recorded | 1,472.4 | 1,792.6 |
| 127 | 26.79 | L-80 | 699.1 | Not recorded | 699.1 | 683.3 | Not recorded | 1,677 | 2,032.8 |
| 127 | 26.79 | N-80 | 699.1 | Not recorded | 699.1 | 683.3 | Not recorded | 1,761.5 | 2,121.8 |
| 127 | 26.79 | C-90 | 786 | Not recorded | 786 | 768.8 | Not recorded | 1,761.5 | 2,152.9 |
| 127 | 26.79 | C-95 | 830.1 | Not recorded | 830.1 | 811.5 | Not recorded | 1,850.5 | 2,277.5 |
| 127 | 26.79 | T-95 | 830.1 | Not recorded | 830.1 | 811.5 | Not recorded | 1,850.5 | 2,277.5 |
| 127 | 26.79 | P-110 | 961.1 | Not recorded | 961.1 | 939.1 | Not recorded | 2,201.9 | 2,695.6 |
| 127 | 26.79 | Q-125 | 1,092.1 | Not recorded | 1,092.1 | 1,067.3 | Not recorded | 2,379.8 | 2,940.3 |
| 127 | 31.85 | L-80 | 843.9 | Not recorded | 745.3 | 683.3 | Not recorded | 2,072.9 | 2,268.6 |
| 127 | 31.85 | N-80 | 843.9 | Not recorded | 745.3 | 683.3 | Not recorded | 2,179.6 | 2,388.7 |

Check every figure against your own pipe records before you pull.

# Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 2 of 2: internal yield and joint strength

| OD mm | Weight kg/m | Grade | Internal yield PE bar | Internal yield STC bar | Internal yield LTC bar | Internal yield BTC bar | Joint STC kN | Joint LTC kN | Joint BTC kN |
|---|---|---|---|---|---|---|---|---|---|
| OD 5 in | | | | | | | | | |
| 127 | 31.85 | C-90 | 949.4 | Not recorded | 839.1 | 768.8 | Not recorded | 2,179.6 | 2,388.7 |
| 127 | 31.85 | C-95 | 1,001.8 | Not recorded | 885.3 | 811.5 | Not recorded | 2,290.8 | 2,504.3 |
| 127 | 31.85 | T-95 | 1,001.8 | Not recorded | 885.3 | 811.5 | Not recorded | 2,290.8 | 2,504.3 |
| 127 | 31.85 | P-110 | 1,159.7 | Not recorded | 1,025.3 | 939.1 | Not recorded | 2,726.8 | 2,984.8 |
| 127 | 31.85 | Q-125 | 1,318.3 | Not recorded | 1,165.2 | 1,067.3 | Not recorded | 2,944.7 | 3,220.5 |
| 127 | 34.53 | L-80 | 922.5 | Not recorded | 745.3 | 683.3 | Not recorded | 2,281.9 | 2,268.6 |
| 127 | 34.53 | N-80 | 922.5 | Not recorded | 745.3 | 683.3 | Not recorded | 2,402 | 2,388.7 |
| 127 | 34.53 | C-90 | 1,038.4 | Not recorded | 839.1 | 768.8 | Not recorded | 2,402 | 2,388.7 |
| 127 | 34.53 | C-95 | 1,095.6 | Not recorded | 885.3 | 811.5 | Not recorded | 2,522.1 | 2,504.3 |
| 127 | 34.53 | T-95 | 1,095.6 | Not recorded | 885.3 | 811.5 | Not recorded | 2,522.1 | 2,504.3 |
| 127 | 34.53 | P-110 | 1,268.6 | Not recorded | 1,019 | 939.5 | Not recorded | 3,002.5 | 2,984.8 |
| 127 | 34.53 | Q-125 | 1,441.7 | Not recorded | 1,165.2 | 1,067.3 | Not recorded | 3,242.8 | 3,220.5 |
| 127 | 35.86 | L-80 | 965.3 | Not recorded | 745.3 | 683.3 | Not recorded | 2,393.1 | 2,268.6 |
| 127 | 35.86 | N-80 | 965.3 | Not recorded | 745.3 | 683.3 | Not recorded | 2,482.1 | 2,388.7 |
| 127 | 35.86 | C-90 | 1,085.9 | Not recorded | 839.1 | 768.8 | Not recorded | 2,522.1 | 2,388.7 |
| 127 | 35.86 | C-95 | 1,146.6 | Not recorded | 885.3 | 811.5 | Not recorded | 2,646.7 | 2,504.3 |
| 127 | 35.86 | T-95 | 1,146.6 | Not recorded | 885.3 | 811.5 | Not recorded | 2,646.7 | 2,504.3 |
| 127 | 35.86 | P-110 | 1,327.2 | Not recorded | 1,025.3 | 939.1 | Not recorded | 3,149.3 | 2,984.8 |
| 127 | 35.86 | Q-125 | 1,508.6 | Not recorded | 1,165.2 | 1,067.3 | Not recorded | 3,402.9 | 3,220.5 |
| OD 5-1/2 in | | | | | | | | | |
| 139.7 | 23.07 | J-55 | 331.6 | 331.6 | 331.6 | 331.6 | 898.5 | 965.3 | 1,334.5 |
| 139.7 | 23.07 | K-55 | 331.6 | 330.9 | 331.6 | 331.6 | 987.5 | 1,063.1 | 1,628 |
| 139.7 | 23.07 | M-65 | 392.3 | 392.3 | 392.3 | 392.3 | 1,045.3 | 1,125.4 | 1,521.3 |
| 139.7 | 25.3 | J-55 | 366.8 | 366.8 | 366.8 | 366.8 | 1,018.6 | 1,098.7 | 1,463.5 |
| 139.7 | 25.3 | K-55 | 366.8 | 366.8 | 366.8 | 366.8 | 1,121 | 1,209.9 | 1,788.2 |

Check every figure against your own pipe records before you pull.

## Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 2 of 2: internal yield and joint strength

| OD mm | Weight kg/m | Grade | Internal yield PE bar | Internal yield STC bar | Internal yield LTC bar | Internal yield BTC bar | Joint STC kN | Joint LTC kN | Joint BTC kN |
|---|---|---|---|---|---|---|---|---|---|
| OD 5-1/2 in | | | | | | | | | |
| 139.7 | 25.3 | M-65 | 433.7 | 433.7 | 433.7 | 433.7 | 1,187.7 | 1,276.6 | 1,672.5 |
| 139.7 | 25.3 | L-80 | 533.7 | Not recorded | 533.7 | 533.7 | Not recorded | 1,503.5 | 1,903.8 |
| 139.7 | 25.3 | N-80 | 533.7 | Not recorded | 533.7 | 533.7 | Not recorded | 1,548 | 1,983.9 |
| 139.7 | 25.3 | C-90 | 600.5 | Not recorded | 600.5 | 600.5 | Not recorded | 1,583.6 | 2,028.4 |
| 139.7 | 25.3 | C-95 | 633.6 | Not recorded | 633.6 | 633.6 | Not recorded | 1,663.6 | 2,135.1 |
| 139.7 | 25.3 | T-95 | 633.6 | Not recorded | 633.6 | 633.6 | Not recorded | 1,663.6 | 2,135.1 |
| 139.7 | 25.3 | P-110 | 733.6 | Not recorded | 733.6 | 733.6 | Not recorded | 1,979.5 | 2,526.6 |
| 139.7 | 25.3 | Q-125 | 833.6 | Not recorded | 833.6 | 833.6 | Not recorded | 2,139.6 | 2,757.9 |
| 139.7 | 29.76 | M-65 | 515 | Not recorded | 515 | 515 | Not recorded | 1,570.2 | 1,966.1 |
| 139.7 | 29.76 | L-80 | 633.6 | Not recorded | 633.6 | 619.8 | Not recorded | 1,850.5 | 2,237.5 |
| 139.7 | 29.76 | N-80 | 633.6 | Not recorded | 633.6 | 619.8 | Not recorded | 1,903.8 | 2,330.9 |
| 139.7 | 29.76 | C-90 | 712.9 | Not recorded | 712.9 | 697.7 | Not recorded | 1,948.3 | 1,939.4 |
| 139.7 | 29.76 | C-95 | 752.2 | Not recorded | 752.2 | 736.4 | Not recorded | 2,046.2 | 2,504.3 |
| 139.7 | 29.76 | T-95 | 752.2 | Not recorded | 752.2 | 736.4 | Not recorded | 2,046.2 | 2,504.3 |
| 139.7 | 29.76 | P-110 | 870.8 | Not recorded | 870.8 | 852.2 | Not recorded | 2,437.6 | 2,967 |
| 139.7 | 29.76 | Q-125 | 990.1 | Not recorded | 990.1 | 968.7 | Not recorded | 2,633.3 | 3,238.3 |
| 139.7 | 34.23 | L-80 | 728.1 | Not recorded | 681.2 | 619.8 | Not recorded | 2,175.2 | 2,446.5 |
| 139.7 | 34.23 | N-80 | 728.1 | Not recorded | 681.2 | 619.8 | Not recorded | 2,233 | 2,575.5 |
| 139.7 | 34.23 | C-90 | 819.1 | Not recorded | 766 | 697.7 | Not recorded | 2,286.4 | 2,575.5 |
| 139.7 | 34.23 | C-95 | 864.6 | Not recorded | 808.8 | 736.4 | Not recorded | 2,402 | 2,704.5 |
| 139.7 | 34.23 | T-95 | 864.6 | Not recorded | 808.8 | 736.4 | Not recorded | 2,402 | 2,704.5 |
| 139.7 | 34.23 | P-110 | 1,001.8 | Not recorded | 936.3 | 852.2 | Not recorded | 2,860.2 | 3,220.5 |
| 139.7 | 34.23 | Q-125 | 1,138.3 | Not recorded | 1,063.9 | 968.7 | Not recorded | 3,087.1 | 3,478.5 |
| 139.7 | 38.69 | C-90 | 939.8 | Not recorded | 766 | 697.7 | Not recorded | 2,660 | 2,575.5 |
| 139.7 | 38.69 | C-95 | 992.2 | Not recorded | 808.8 | 736.4 | Not recorded | 2,793.5 | 2,704.5 |

Check every figure against your own pipe records before you pull.

# Casingjacks

Casingjacks LLC | sales@casingjack.com

## Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 2 of 2: internal yield and joint strength

| OD mm | Weight kg/m | Grade | Internal yield PE bar | Internal yield STC bar | Internal yield LTC bar | Internal yield BTC bar | Joint STC kN | Joint LTC kN | Joint BTC kN |
|---|---|---|---|---|---|---|---|---|---|
| OD 5-1/2 in | | | | | | | | | |
| 139.7 | 38.69 | T-95 | 992.2 | Not recorded | 808.8 | 736.4 | Not recorded | 2,793.5 | 2,704.5 |
| 139.7 | 38.69 | P-110 | 1,148.7 | Not recorded | 936.3 | 852.2 | Not recorded | 3,327.3 | 3,220.5 |
| 139.7 | 38.69 | Q-125 | 1,305.2 | Not recorded | 1,063.9 | 968.7 | Not recorded | 3,594.2 | 3,478.5 |
| 139.7 | 39.88 | C-90 | 987.3 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 139.7 | 39.88 | T-95 | 1,041.8 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 139.7 | 44.2 | C-90 | 1,109.4 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 139.7 | 44.2 | T-95 | 1,171.4 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 139.7 | 48.51 | C-90 | 1,234.2 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 139.7 | 48.51 | T-95 | 1,296.9 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 139.7 | 52.53 | C-90 | 1,356.2 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 139.7 | 52.53 | T-95 | 1,432 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 139.7 | 56.55 | C-90 | 1,481 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 139.7 | 56.55 | T-95 | 1,563 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 139.7 | 60.27 | C-90 | 1,603 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 139.7 | 60.27 | T-95 | 1,692 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 139.7 | 64.14 | C-90 | 1,727.8 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 139.7 | 64.14 | T-95 | 1,823.7 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| OD 5-5/8 in | | | | | | | | | |
| 142.9 | 39.73 | L-80 | 818.4 | Not recorded | 681.2 | 619.8 | Not recorded | 2,170.7 | 2,446.5 |
| 142.9 | 39.73 | P-110 | 1,125.2 | Not recorded | 936.3 | 852.2 | Not recorded | 2,855.8 | 3,220.5 |
| OD 5-3/4 in | | | | | | | | | |
| 146 | 26.94 | J-55 | 350.9 | Not recorded | Not recorded | 350.9 | Not recorded | Not recorded | 1,530.2 |
| 146 | 26.94 | L-80 | 510.2 | Not recorded | Not recorded | 510.2 | Not recorded | Not recorded | 1,988.4 |
| 146 | 26.94 | N-80 | 510.2 | Not recorded | Not recorded | 510.2 | Not recorded | Not recorded | 2,072.9 |
| 146 | 26.94 | P-110 | 701.9 | Not recorded | Not recorded | 701.9 | Not recorded | Not recorded | 2,642.2 |

Check every figure against your own pipe records before you pull.

## Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 2 of 2: internal yield and joint strength

| OD mm | Weight kg/m | Grade | Internal yield PE bar | Internal yield STC bar | Internal yield LTC bar | Internal yield BTC bar | Joint STC kN | Joint LTC kN | Joint BTC kN |
|---|---|---|---|---|---|---|---|---|---|
| OD 5-3/4 in | | | | | | | | | |
| 146 | 29.32 | J-55 | 386.8 | Not recorded | Not recorded | 386.8 | Not recorded | Not recorded | 1,677 |
| 146 | 29.32 | L-80 | 562.6 | Not recorded | Not recorded | 562.6 | Not recorded | Not recorded | 2,179.6 |
| 146 | 29.32 | N-80 | 562.6 | Not recorded | Not recorded | 562.6 | Not recorded | Not recorded | 2,273 |
| 146 | 29.32 | P-110 | 773.6 | Not recorded | Not recorded | 773.6 | Not recorded | Not recorded | 2,895.8 |
| 146 | 32.44 | L-80 | 629.5 | Not recorded | Not recorded | 629.5 | Not recorded | Not recorded | 2,424.3 |
| 146 | 32.44 | N-80 | 629.5 | Not recorded | Not recorded | 629.5 | Not recorded | Not recorded | 2,526.6 |
| 146 | 32.44 | P-110 | 865.3 | Not recorded | Not recorded | 865.3 | Not recorded | Not recorded | 3,216.1 |
| 146 | 36.01 | L-80 | 705.3 | Not recorded | Not recorded | 705.3 | Not recorded | Not recorded | 2,691.2 |
| 146 | 36.01 | N-80 | 705.3 | Not recorded | Not recorded | 705.3 | Not recorded | Not recorded | 2,802.4 |
| 146 | 36.01 | P-110 | 969.4 | Not recorded | Not recorded | 969.4 | Not recorded | Not recorded | 3,571.9 |
| OD 6-5/8 in | | | | | | | | | |
| 168.3 | 29.76 | H-40 | 209.6 | 209.6 | Not recorded | Not recorded | 818.5 | Not recorded | Not recorded |
| 168.3 | 29.76 | J-55 | 288.2 | 288.2 | 288.2 | 288.2 | 1,089.8 | 1,183.2 | 1,663.6 |
| 168.3 | 29.76 | K-55 | 288.2 | 288.2 | 288.2 | 288.2 | 1,187.7 | 1,290 | 2,015 |
| 168.3 | 29.76 | M-65 | 340.6 | 340.6 | 340.6 | 340.6 | 1,267.7 | 1,374.5 | 1,903.8 |
| 168.3 | 35.72 | J-55 | 352.3 | 352.3 | 352.3 | 352.3 | 1,396.7 | 1,512.4 | 2,015 |
| 168.3 | 35.72 | K-55 | 352.3 | 352.3 | 352.3 | 352.3 | 1,521.3 | 1,654.7 | 2,437.6 |
| 168.3 | 35.72 | M-65 | 416.4 | 416.4 | 416.4 | 416.4 | 1,628 | 1,765.9 | 2,304.2 |
| 168.3 | 35.72 | L-80 | 513 | Not recorded | 513 | 513 | Not recorded | 2,104 | 2,633.3 |
| 168.3 | 35.72 | C-90 | 577.1 | Not recorded | 577.1 | 577.1 | Not recorded | 2,313.1 | 2,815.7 |
| 168.3 | 35.72 | C-95 | 608.8 | Not recorded | 608.8 | 608.8 | Not recorded | 2,428.7 | 2,958.1 |
| 168.3 | 35.72 | P-110 | 705.3 | Not recorded | 705.3 | 705.3 | Not recorded | 2,851.3 | 3,496.3 |
| 168.3 | 41.67 | M-65 | 493.7 | Not recorded | 493.7 | 493.7 | Not recorded | 2,148.5 | 2,700.1 |
| 168.3 | 41.67 | L-80 | 607.4 | Not recorded | 607.4 | 607.4 | Not recorded | 2,562.2 | 3,082.6 |
| 168.3 | 41.67 | N-80 | 607.4 | Not recorded | 607.4 | 607.4 | Not recorded | 2,606.7 | 3,207.2 |

Check every figure against your own pipe records before you pull.

# Casingjacks

Casingjacks LLC | sales@casingjack.com

## Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 2 of 2: internal yield and joint strength

| OD mm | Weight kg/m | Grade | Internal yield PE bar | Internal yield STC bar | Internal yield LTC bar | Internal yield BTC bar | Joint STC kN | Joint LTC kN | Joint BTC kN |
|---|---|---|---|---|---|---|---|---|---|
| OD 6-5/8 in | | | | | | | | | |
| 168.3 | 41.67 | C-90 | 683.3 | Not recorded | 683.3 | 683.3 | Not recorded | 2,815.7 | 3,300.6 |
| 168.3 | 41.67 | C-95 | 721.2 | Not recorded | 721.2 | 721.2 | Not recorded | 2,958.1 | 3,469.6 |
| 168.3 | 41.67 | P-110 | 835.6 | Not recorded | 835.6 | 835.6 | Not recorded | 3,474.1 | 4,101.3 |
| 168.3 | 47.62 | L-80 | 692.2 | Not recorded | 692.2 | 677.1 | Not recorded | 2,962.5 | 3,483 |
| 168.3 | 47.62 | N-80 | 692.2 | Not recorded | 692.2 | 677.1 | Not recorded | 3,011.4 | 3,620.9 |
| 168.3 | 47.62 | C-90 | 778.4 | Not recorded | 778.4 | 761.9 | Not recorded | 3,256.1 | 3,723.2 |
| 168.3 | 47.62 | C-95 | 821.9 | Not recorded | 821.9 | 803.9 | Not recorded | 3,420.7 | 3,914.4 |
| 168.3 | 47.62 | P-110 | 951.5 | Not recorded | 951.5 | 930.8 | Not recorded | 4,021.2 | 4,626.2 |
| 168.3 | 47.62 | Q-125 | 1,081.1 | Not recorded | 1,081.1 | 1,057.7 | Not recorded | 4,399.3 | 5,062.1 |
| OD 7 in | | | | | | | | | |
| 177.8 | 29.76 | H-40 | 187.5 | 187.5 | Not recorded | Not recorded | 782.9 | Not recorded | Not recorded |
| 177.8 | 29.76 | J-55 | 257.9 | 257.9 | 257.9 | 257.9 | 1,040.9 | 1,143.2 | 1,659.2 |
| 177.8 | 29.76 | K-55 | 257.9 | 257.9 | 257.9 | 257.9 | 1,129.8 | 1,250 | 2,006.1 |
| 177.8 | 29.76 | M-65 | 304.7 | 304.7 | 304.7 | 304.7 | 1,209.9 | 1,334.5 | 1,899.4 |
| 177.8 | 34.23 | J-55 | 300.6 | 300.6 | 300.6 | 300.6 | 1,263.3 | 1,392.3 | 1,921.6 |
| 177.8 | 34.23 | K-55 | 300.6 | 300.6 | 300.6 | 300.6 | 1,374.5 | 1,516.8 | 2,322 |
| 177.8 | 34.23 | M-65 | 355.1 | 355.1 | 355.1 | 355.1 | 1,472.4 | 1,619.2 | 2,197.4 |
| 177.8 | 34.23 | L-80 | 437.1 | Not recorded | 437.1 | 437.1 | Not recorded | 1,935 | 2,513.2 |
| 177.8 | 34.23 | N-80 | 437.1 | Not recorded | 437.1 | 437.1 | Not recorded | 1,966.1 | 2,615.6 |
| 177.8 | 34.23 | C-90 | 491.6 | Not recorded | 491.6 | 491.6 | Not recorded | 2,130.7 | 2,691.2 |
| 177.8 | 34.23 | C-95 | 519.2 | Not recorded | 519.2 | 519.2 | Not recorded | 2,246.4 | 2,829.1 |
| 177.8 | 34.23 | T-95 | 519.2 | Not recorded | 519.2 | 519.2 | Not recorded | 2,246.4 | 2,829.1 |
| 177.8 | 38.69 | J-55 | 343.4 | 343.4 | 343.4 | 343.4 | 1,485.7 | 1,632.5 | 2,179.6 |
| 177.8 | 38.69 | K-55 | 343.4 | 343.4 | 343.4 | 343.4 | 1,619.2 | 1,783.7 | 2,633.3 |
| 177.8 | 38.69 | M-65 | 405.4 | 405.4 | 405.4 | 405.4 | 1,730.4 | 1,903.8 | 2,495.5 |

Check every figure against your own pipe records before you pull.

## Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 2 of 2: internal yield and joint strength

| OD mm | Weight kg/m | Grade | Internal yield PE bar | Internal yield STC bar | Internal yield LTC bar | Internal yield BTC bar | Joint STC kN | Joint LTC kN | Joint BTC kN |
|---|---|---|---|---|---|---|---|---|---|
| OD 7 in | | | | | | | | | |
| 177.8 | 38.69 | L-80 | 499.2 | Not recorded | 499.2 | 499.2 | Not recorded | 2,273 | 2,851.3 |
| 177.8 | 38.69 | N-80 | 499.2 | Not recorded | 499.2 | 499.2 | Not recorded | 2,308.6 | 2,967 |
| 177.8 | 38.69 | C-90 | 561.2 | Not recorded | 561.2 | 561.2 | Not recorded | 2,504.3 | 3,055.9 |
| 177.8 | 38.69 | C-95 | 592.9 | Not recorded | 592.9 | 592.9 | Not recorded | 2,637.8 | 3,211.6 |
| 177.8 | 38.69 | T-95 | 592.9 | Not recorded | 592.9 | 592.9 | Not recorded | 2,637.8 | 3,211.6 |
| 177.8 | 38.69 | P-110 | 686 | Not recorded | 686 | 686 | Not recorded | 2,842.4 | 3,794.3 |
| 177.8 | 43.16 | M-65 | 457.1 | Not recorded | 457.1 | 457.1 | Not recorded | 2,188.5 | 2,793.5 |
| 177.8 | 43.16 | L-80 | 562.6 | Not recorded | 562.6 | 562.6 | Not recorded | 2,611.1 | 3,193.8 |
| 177.8 | 43.16 | N-80 | 562.6 | Not recorded | 562.6 | 562.6 | Not recorded | 2,655.6 | 3,318.4 |
| 177.8 | 43.16 | C-90 | 632.9 | Not recorded | 632.9 | 632.9 | Not recorded | 2,882.4 | 3,416.2 |
| 177.8 | 43.16 | C-95 | 668.1 | Not recorded | 668.1 | 668.1 | Not recorded | 3,038.1 | 3,594.2 |
| 177.8 | 43.16 | T-95 | 668.1 | Not recorded | 668.1 | 668.1 | Not recorded | 3,038.1 | 3,594.2 |
| 177.8 | 43.16 | P-110 | 773.6 | Not recorded | 773.6 | 773.6 | Not recorded | 3,545.2 | 4,248.1 |
| 177.8 | 43.16 | Q-125 | 879.1 | Not recorded | 879.1 | 879.1 | Not recorded | 3,936.7 | 4,648.4 |
| 177.8 | 47.62 | L-80 | 624.7 | Not recorded | 624.7 | 583.3 | Not recorded | 2,940.3 | 3,518.5 |
| 177.8 | 47.62 | N-80 | 624.7 | Not recorded | 624.7 | 583.3 | Not recorded | 2,989.2 | 3,660.9 |
| 177.8 | 47.62 | C-90 | 702.6 | Not recorded | 702.6 | 656.4 | Not recorded | 3,242.8 | 3,767.6 |
| 177.8 | 47.62 | C-95 | 741.9 | Not recorded | 741.9 | 692.9 | Not recorded | 3,416.2 | 3,963.4 |
| 177.8 | 47.62 | T-95 | 741.9 | Not recorded | 741.9 | 692.9 | Not recorded | 3,416.2 | 3,963.4 |
| 177.8 | 47.62 | P-110 | 859.1 | Not recorded | 859.1 | 802.5 | Not recorded | 3,990.1 | 4,684 |
| 177.8 | 47.62 | Q-125 | 976.3 | Not recorded | 976.3 | 911.5 | Not recorded | 4,430.4 | 5,124.4 |
| 177.8 | 52.09 | L-80 | 686.7 | Not recorded | 637.1 | 583.3 | Not recorded | 3,265 | 3,705.4 |
| 177.8 | 52.09 | N-80 | 686.7 | Not recorded | 637.1 | 583.3 | Not recorded | 3,318.4 | 3,896.6 |
| 177.8 | 52.09 | C-90 | 772.9 | Not recorded | 716.4 | 656.4 | Not recorded | 3,598.6 | 3,896.6 |
| 177.8 | 52.09 | C-95 | 815.6 | Not recorded | 756.4 | 692.9 | Not recorded | 3,794.3 | 4,092.4 |

Check every figure against your own pipe records before you pull.

## Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 2 of 2: internal yield and joint strength

| OD mm | Weight kg/m | Grade | Internal yield PE bar | Internal yield STC bar | Internal yield LTC bar | Internal yield BTC bar | Joint STC kN | Joint LTC kN | Joint BTC kN |
|---|---|---|---|---|---|---|---|---|---|
| OD 7 in | | | | | | | | | |
| 177.8 | 52.09 | T-95 | 815.6 | Not recorded | 756.4 | 692.9 | Not recorded | 3,794.3 | 4,092.4 |
| 177.8 | 52.09 | P-110 | 944.6 | Not recorded | 875.6 | 802.5 | Not recorded | 4,430.4 | 4,875.3 |
| 177.8 | 52.09 | Q-125 | 1,072.8 | Not recorded | 994.9 | 911.5 | Not recorded | 4,919.7 | 5,262.2 |
| 177.8 | 56.55 | L-80 | 744.6 | Not recorded | 637.1 | 583.3 | Not recorded | 3,563 | 3,700.9 |
| 177.8 | 56.55 | N-80 | 744.6 | Not recorded | 637.1 | 583.3 | Not recorded | 3,620.9 | 3,896.6 |
| 177.8 | 56.55 | C-90 | 837.7 | Not recorded | 716.4 | 656.4 | Not recorded | 3,927.8 | 3,896.6 |
| 177.8 | 56.55 | C-95 | 884.6 | Not recorded | 756.4 | 692.9 | Not recorded | 4,141.3 | 4,092.4 |
| 177.8 | 56.55 | T-95 | 884.6 | Not recorded | 756.4 | 692.9 | Not recorded | 4,141.3 | 4,092.4 |
| 177.8 | 56.55 | P-110 | 1,023.9 | Not recorded | 875.6 | 802.5 | Not recorded | 4,835.2 | 4,875.3 |
| 177.8 | 56.55 | Q-125 | 1,163.8 | Not recorded | 994.9 | 911.5 | Not recorded | 5,369 | 5,262.2 |
| 177.8 | 61.01 | C-90 | 915.6 | Not recorded | 716.4 | 656.4 | Not recorded | 4,016.7 | 3,896.6 |
| 177.8 | 61.01 | T-95 | 966 | Not recorded | 756.4 | 692.9 | Not recorded | 4,234.7 | 4,092.4 |
| 177.8 | 61.01 | P-110 | 1,119 | Not recorded | 875.6 | 802.5 | Not recorded | 4,942 | 4,875.3 |
| 177.8 | 61.01 | Q-125 | 1,271.4 | Not recorded | 994.9 | 911.5 | Not recorded | 5,533.6 | 5,262.2 |
| 177.8 | 63.54 | C-90 | 969.4 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 177.8 | 63.54 | T-95 | 1,023.2 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 177.8 | 69.05 | C-90 | 1,065.9 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 177.8 | 69.05 | T-95 | 1,125.2 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 177.8 | 74.56 | C-90 | 1,163.8 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 177.8 | 74.56 | T-95 | 1,228 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 177.8 | 79.77 | C-90 | 1,259.7 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 177.8 | 79.77 | T-95 | 1,330 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 177.8 | 84.97 | C-90 | 1,357.6 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 177.8 | 84.97 | T-95 | 1,432.7 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |

# Casingjacks

Casingjacks LLC | sales@casingjack.com

## Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 2 of 2: internal yield and joint strength

| OD mm | Weight kg/m | Grade | Internal yield PE bar | Internal yield STC bar | Internal yield LTC bar | Internal yield BTC bar | Joint STC kN | Joint LTC kN | Joint BTC kN |
|---|---|---|---|---|---|---|---|---|---|
| OD 7-5/8 in | | | | | | | | | |
| 193.7 | 35.72 | H-40 | 189.6 | 189.6 | Not recorded | Not recorded | 943 | Not recorded | Not recorded |
| 193.7 | 39.29 | J-55 | 285.4 | 285.4 | 285.4 | 285.4 | 1,401.2 | 1,539.1 | 2,148.5 |
| 193.7 | 39.29 | K-55 | 285.4 | 285.4 | 285.4 | 285.4 | 1,521.3 | 1,677 | 2,584.4 |
| 193.7 | 39.29 | M-65 | 337.2 | 337.2 | 337.2 | 337.2 | 1,636.9 | 1,792.6 | 2,464.3 |
| 193.7 | 39.29 | L-80 | 415.1 | Not recorded | 415.1 | 415.1 | Not recorded | 2,144 | 2,824.6 |
| 193.7 | 39.29 | N-80 | 415.1 | Not recorded | 415.1 | 415.1 | Not recorded | 2,179.6 | 2,931.4 |
| 193.7 | 39.29 | C-90 | 467.5 | Not recorded | 467.5 | 467.5 | Not recorded | 2,366.5 | 3,029.2 |
| 193.7 | 39.29 | C-95 | 493 | Not recorded | 493 | 493 | Not recorded | 2,491 | 3,184.9 |
| 193.7 | 39.29 | T-95 | 493 | Not recorded | 493 | 486.1 | Not recorded | 2,491 | 3,184.9 |
| 193.7 | 39.29 | P-110 | 570.9 | Not recorded | 570.9 | 570.9 | Not recorded | 2,909.1 | 3,758.7 |
| 193.7 | 44.2 | M-65 | 385.4 | Not recorded | 385.4 | 385.4 | Not recorded | 2,108.5 | 2,797.9 |
| 193.7 | 44.2 | L-80 | 475 | Not recorded | 475 | 475 | Not recorded | 2,517.7 | 3,207.2 |
| 193.7 | 44.2 | N-80 | 475 | Not recorded | 475 | 475 | Not recorded | 2,557.7 | 3,331.7 |
| 193.7 | 44.2 | C-90 | 534.3 | Not recorded | 534.3 | 534.3 | Not recorded | 2,780.1 | 3,438.5 |
| 193.7 | 44.2 | C-95 | 564 | Not recorded | 564 | 564 | Not recorded | 2,931.4 | 3,616.4 |
| 193.7 | 44.2 | T-95 | 564 | Not recorded | 564 | 564 | Not recorded | 2,931.4 | 3,616.4 |
| 193.7 | 44.2 | P-110 | 652.9 | Not recorded | 652.9 | 652.9 | Not recorded | 3,420.7 | 4,270.3 |
| 193.7 | 50.15 | L-80 | 544.7 | Not recorded | 544.7 | 544.7 | Not recorded | 2,953.6 | 3,647.5 |
| 193.7 | 50.15 | N-80 | 544.7 | Not recorded | 544.7 | 544.7 | Not recorded | 2,998.1 | 3,789.9 |
| 193.7 | 50.15 | C-90 | 612.3 | Not recorded | 612.3 | 612.3 | Not recorded | 3,260.5 | 3,914.4 |
| 193.7 | 50.15 | C-95 | 646.7 | Not recorded | 646.7 | 646.7 | Not recorded | 3,434 | 4,114.6 |
| 193.7 | 50.15 | T-95 | 646.7 | Not recorded | 646.7 | 646.7 | Not recorded | 3,434 | 4,114.6 |
| 193.7 | 50.15 | P-110 | 748.8 | Not recorded | 748.8 | 748.8 | Not recorded | 4,007.8 | 4,861.9 |
| 193.7 | 50.15 | Q-125 | 850.8 | Not recorded | 850.8 | 850.8 | Not recorded | 4,488.3 | 5,324.5 |
| 193.7 | 58.04 | L-80 | 632.9 | Not recorded | 632.9 | 632.9 | Not recorded | 3,496.3 | 4,203.6 |

Check every figure against your own pipe records before you pull.

## Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 2 of 2: internal yield and joint strength

| OD mm | Weight kg/m | Grade | Internal yield PE bar | Internal yield STC bar | Internal yield LTC bar | Internal yield BTC bar | Joint STC kN | Joint LTC kN | Joint BTC kN |
|---|---|---|---|---|---|---|---|---|---|
| OD 7-5/8 in | | | | | | | | | |
| 193.7 | 58.04 | N-80 | 632.9 | Not recorded | 632.9 | 632.9 | Not recorded | 3,549.7 | 4,363.7 |
| 193.7 | 58.04 | C-90 | 712.2 | Not recorded | 712.2 | 712.2 | Not recorded | 3,856.6 | 4,506 |
| 193.7 | 58.04 | C-95 | 751.5 | Not recorded | 751.5 | 751.5 | Not recorded | 4,065.7 | 4,737.4 |
| 193.7 | 58.04 | T-95 | 751.5 | Not recorded | 751.5 | 751.5 | Not recorded | 4,065.7 | 4,737.4 |
| 193.7 | 58.04 | P-110 | 870.1 | Not recorded | 870.1 | 870.1 | Not recorded | 4,741.8 | 5,595.9 |
| 193.7 | 58.04 | Q-125 | 988.7 | Not recorded | 988.7 | 988.7 | Not recorded | 5,311.2 | 6,134.1 |
| 193.7 | 63.69 | L-80 | 711.5 | Not recorded | 711.5 | 675 | Not recorded | 3,963.4 | 4,684 |
| 193.7 | 63.69 | N-80 | 711.5 | Not recorded | 711.5 | 675 | Not recorded | 4,025.6 | 4,861.9 |
| 193.7 | 63.69 | C-90 | 800.5 | Not recorded | 800.5 | 759.1 | Not recorded | 4,372.6 | 5,022 |
| 193.7 | 63.69 | C-95 | 844.6 | Not recorded | 844.6 | 801.2 | Not recorded | 4,612.8 | 5,280 |
| 193.7 | 63.69 | T-95 | 844.6 | Not recorded | 844.6 | 801.2 | Not recorded | 4,612.8 | 5,280 |
| 193.7 | 63.69 | P-110 | 978.4 | Not recorded | 978.4 | 928 | Not recorded | 5,382.3 | 6,236.4 |
| 193.7 | 63.69 | Q-125 | 1,111.4 | Not recorded | 1,111.4 | 1,054.2 | Not recorded | 6,027.3 | 6,832.5 |
| 193.7 | 67.41 | L-80 | 752.9 | Not recorded | 723.3 | 675 | Not recorded | 4,212.5 | 4,933.1 |
| 193.7 | 67.41 | N-80 | 752.9 | Not recorded | 723.3 | 675 | Not recorded | 4,279.2 | 5,124.4 |
| 193.7 | 67.41 | C-90 | 847.4 | Not recorded | 814.3 | 759.1 | Not recorded | 4,648.4 | 5,288.9 |
| 193.7 | 67.41 | C-95 | 894.3 | Not recorded | 859.1 | 801.2 | Not recorded | 4,897.5 | 5,564.7 |
| 193.7 | 67.41 | P-110 | 1,035.6 | Not recorded | 994.9 | 928 | Not recorded | 5,716 | 6,570 |
| 193.7 | 67.41 | Q-125 | 1,176.9 | Not recorded | 1,130.7 | 1,054.2 | Not recorded | 6,401 | 7,201.7 |
| 193.7 | 70.09 | L-80 | 791.5 | Not recorded | 723.3 | 675 | Not recorded | 4,434.9 | 5,159.9 |
| 193.7 | 70.09 | N-80 | 791.5 | Not recorded | 723.3 | 675 | Not recorded | 4,506 | 5,360.1 |
| 193.7 | 70.09 | C-90 | 890.1 | Not recorded | 814.3 | 759.1 | Not recorded | 4,893 | 5,506.9 |
| 193.7 | 70.09 | C-95 | 939.8 | Not recorded | 859.1 | 801.2 | Not recorded | 5,155.5 | 5,782.7 |
| 193.7 | 70.09 | T-95 | 939.8 | Not recorded | 859.1 | 801.2 | Not recorded | 5,155.5 | 5,782.7 |
| 193.7 | 70.09 | P-110 | 1,088 | Not recorded | 994.9 | 928 | Not recorded | 6,018.4 | 6,872.5 |

Check every figure against your own pipe records before you pull.

# Casingjacks

Casingjacks LLC | sales@casingjack.com

## Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 2 of 2: internal yield and joint strength

| OD mm | Weight kg/m | Grade | Internal yield PE bar | Internal yield STC bar | Internal yield LTC bar | Internal yield BTC bar | Joint STC kN | Joint LTC kN | Joint BTC kN |
|---|---|---|---|---|---|---|---|---|---|
| OD 7-5/8 in | | | | | | | | | |
| 193.7 | 70.09 | Q-125 | 1,236.2 | Not recorded | 1,130.7 | 1,054.2 | Not recorded | 6,739.1 | 7,437.4 |
| 193.7 | 76.19 | C-90 | 978.4 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 193.7 | 76.19 | T-95 | 1,032.8 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 193.7 | 82.3 | C-90 | 1,068 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 193.7 | 82.3 | T-95 | 1,127.3 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| OD 7-3/4 in | | | | | | | | | |
| 196.8 | 68.6 | L-80 | 741.2 | Not recorded | 723.3 | 675 | Not recorded | 3,741 | 4,452.7 |
| 196.8 | 68.6 | C-90 | 833.6 | Not recorded | 814.3 | 759.1 | Not recorded | 4,127.9 | 4,777.4 |
| 196.8 | 68.6 | C-95 | 879.8 | Not recorded | 859.1 | 801.2 | Not recorded | 4,350.4 | 5,022 |
| 196.8 | 68.6 | T-95 | 879.8 | Not recorded | 859.1 | 801.2 | Not recorded | 4,350.4 | 5,022 |
| 196.8 | 68.6 | P-110 | 1,019 | Not recorded | 994.9 | 928 | Not recorded | 5,079.9 | 5,933.9 |
| 196.8 | 68.6 | Q-125 | 1,157.6 | Not recorded | 1,130.7 | 1,054.2 | Not recorded | 5,689.3 | 6,503.3 |
| OD 8-5/8 in | | | | | | | | | |
| 219.1 | 35.72 | J-55 | 203.4 | 203.4 | Not recorded | Not recorded | 1,085.4 | Not recorded | Not recorded |
| 219.1 | 35.72 | K-55 | 203.4 | 203.4 | Not recorded | Not recorded | 1,169.9 | Not recorded | Not recorded |
| 219.1 | 35.72 | M-65 | 239.9 | 239.9 | Not recorded | Not recorded | 1,343.4 | Not recorded | Not recorded |
| 219.1 | 41.67 | H-40 | 170.3 | 170.3 | Not recorded | Not recorded | 1,036.4 | Not recorded | Not recorded |
| 219.1 | 47.62 | H-40 | 197.2 | 197.2 | Not recorded | Not recorded | 1,241.1 | Not recorded | Not recorded |
| 219.1 | 47.62 | J-55 | 271 | 271 | 271 | 271 | 1,654.7 | 1,854.9 | 2,575.5 |
| 219.1 | 47.62 | K-55 | 271 | 271 | 271 | 271 | 1,788.2 | 2,010.6 | 3,069.3 |
| 219.1 | 47.62 | M-65 | 319.9 | 319.9 | 319.9 | 319.9 | 1,935 | 2,166.3 | 2,953.6 |
| 219.1 | 53.57 | J-55 | 307.5 | 307.5 | 307.5 | 307.5 | 1,930.5 | 2,161.8 | 2,909.1 |
| 219.1 | 53.57 | K-55 | 307.5 | 307.5 | 307.5 | 307.5 | 2,081.8 | 2,339.8 | 3,469.6 |
| 219.1 | 53.57 | M-65 | 364 | 364 | 364 | 364 | 2,250.8 | 2,522.1 | 3,340.6 |
| 219.1 | 53.57 | L-80 | 447.5 | Not recorded | 447.5 | 447.5 | Not recorded | 3,015.9 | 3,843.3 |

Check every figure against your own pipe records before you pull.

# Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 2 of 2: internal yield and joint strength

| OD mm | Weight kg/m | Grade | Internal yield PE bar | Internal yield STC bar | Internal yield LTC bar | Internal yield BTC bar | Joint STC kN | Joint LTC kN | Joint BTC kN |
|---|---|---|---|---|---|---|---|---|---|
| OD 8-5/8 in | | | | | | | | | |
| 219.1 | 53.57 | N-80 | 447.5 | Not recorded | 447.5 | 447.5 | Not recorded | 3,060.4 | 3,981.2 |
| 219.1 | 59.53 | M-65 | 408.9 | Not recorded | 408.9 | 408.9 | Not recorded | 2,886.9 | 3,732.1 |
| 219.1 | 59.53 | L-80 | 503.3 | Not recorded | 503.3 | 503.3 | Not recorded | 3,451.8 | 4,297 |
| 219.1 | 59.53 | N-80 | 503.3 | Not recorded | 503.3 | 503.3 | Not recorded | 3,505.2 | 4,452.7 |
| 219.1 | 59.53 | C-90 | 566.7 | Not recorded | 566.7 | 566.7 | Not recorded | 3,816.6 | 4,617.3 |
| 219.1 | 59.53 | C-95 | 597.8 | Not recorded | 597.8 | 597.8 | Not recorded | 4,021.2 | 4,857.5 |
| 219.1 | 59.53 | T-95 | 597.8 | Not recorded | 597.8 | 597.8 | Not recorded | 4,021.2 | 4,857.5 |
| 219.1 | 59.53 | P-110 | 692.2 | Not recorded | 692.2 | 692.2 | Not recorded | 4,692.9 | 5,462.4 |
| 219.1 | 65.48 | L-80 | 559.9 | Not recorded | 559.9 | 559.9 | Not recorded | 3,887.7 | 4,741.8 |
| 219.1 | 65.48 | N-80 | 559.9 | Not recorded | 559.9 | 559.9 | Not recorded | 3,945.6 | 4,915.3 |
| 219.1 | 65.48 | C-90 | 629.5 | Not recorded | 629.5 | 629.5 | Not recorded | 4,292.5 | 5,097.7 |
| 219.1 | 65.48 | C-95 | 664.7 | Not recorded | 664.7 | 664.7 | Not recorded | 4,523.8 | 5,364.6 |
| 219.1 | 65.48 | T-95 | 664.7 | Not recorded | 664.7 | 664.7 | Not recorded | 4,523.8 | 5,364.6 |
| 219.1 | 65.48 | P-110 | 769.5 | Not recorded | 769.5 | 769.5 | Not recorded | 5,275.6 | 6,329.8 |
| 219.1 | 65.48 | Q-125 | 874.3 | Not recorded | 874.3 | 874.3 | Not recorded | 5,916.1 | 6,948.1 |
| 219.1 | 72.92 | L-80 | 623.3 | Not recorded | 623.3 | 623.3 | Not recorded | 4,372.6 | 5,248.9 |
| 219.1 | 72.92 | N-80 | 623.3 | Not recorded | 623.3 | 623.3 | Not recorded | 4,434.9 | 5,435.7 |
| 219.1 | 72.92 | C-95 | 740.5 | Not recorded | 740.5 | 740.5 | Not recorded | 5,088.8 | 5,933.9 |
| 219.1 | 72.92 | T-95 | 740.5 | Not recorded | 740.5 | 740.5 | Not recorded | 5,088.8 | 5,933.9 |
| 219.1 | 72.92 | P-110 | 857 | Not recorded | 857 | 857 | Not recorded | 5,938.4 | 7,001.5 |
| 219.1 | 72.92 | Q-125 | 974.2 | Not recorded | 974.2 | 974.2 | Not recorded | 6,654.5 | 7,686.5 |
| OD 9-5/8 in | | | | | | | | | |
| 244.5 | 48.07 | H-40 | 156.5 | 156.5 | Not recorded | Not recorded | 1,129.8 | Not recorded | Not recorded |
| 244.5 | 53.57 | H-40 | 176.5 | 176.5 | Not recorded | Not recorded | 1,307.8 | Not recorded | Not recorded |
| 244.5 | 53.57 | J-55 | 242.7 | 242.7 | 242.7 | 242.7 | 1,752.6 | 2,015 | 2,842.4 |

Check every figure against your own pipe records before you pull.

## Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 2 of 2: internal yield and joint strength

| OD mm | Weight kg/m | Grade | Internal yield PE bar | Internal yield STC bar | Internal yield LTC bar | Internal yield BTC bar | Joint STC kN | Joint LTC kN | Joint BTC kN |
|---|---|---|---|---|---|---|---|---|---|
| OD 9-5/8 in | | | | | | | | | |
| 244.5 | 53.57 | K-55 | 242.7 | 242.7 | 242.7 | 242.7 | 1,881.6 | 2,175.2 | 3,358.4 |
| 244.5 | 53.57 | M-65 | 286.8 | 286.8 | 286.8 | 286.8 | 2,046.2 | 2,353.1 | 3,265 |
| 244.5 | 59.53 | J-55 | 272.3 | 272.3 | 272.3 | 272.3 | 2,010.6 | 2,313.1 | 3,176 |
| 244.5 | 59.53 | K-55 | 272.3 | 272.3 | 272.3 | 272.3 | 2,161.8 | 2,495.5 | 3,749.9 |
| 244.5 | 59.53 | M-65 | 322 | 322 | 322 | 322 | 2,348.7 | 2,704.5 | 3,660.9 |
| 244.5 | 59.53 | L-80 | 396.4 | Not recorded | 396.4 | 396.4 | Not recorded | 3,233.9 | 4,212.5 |
| 244.5 | 59.53 | N-80 | 396.4 | Not recorded | 396.4 | 396.4 | Not recorded | 3,278.3 | 4,354.8 |
| 244.5 | 59.53 | C-90 | 445.4 | Not recorded | 445.4 | 445.4 | Not recorded | 3,576.4 | 4,541.6 |
| 244.5 | 59.53 | C-95 | 470.2 | Not recorded | 470.2 | 470.2 | Not recorded | 3,767.6 | 4,777.4 |
| 244.5 | 59.53 | T-95 | 470.2 | Not recorded | 470.2 | 470.2 | Not recorded | 3,767.6 | 4,777.4 |
| 244.5 | 64.74 | M-65 | 354.4 | Not recorded | 354.4 | 354.4 | Not recorded | 3,020.3 | 3,999 |
| 244.5 | 64.74 | L-80 | 436.4 | Not recorded | 436.4 | 436.4 | Not recorded | 3,616.4 | 4,617.3 |
| 244.5 | 64.74 | N-80 | 436.4 | Not recorded | 436.4 | 436.4 | Not recorded | 3,669.8 | 4,777.4 |
| 244.5 | 64.74 | C-90 | 490.9 | Not recorded | 490.9 | 490.9 | Not recorded | 3,999 | 4,977.6 |
| 244.5 | 64.74 | C-95 | 517.8 | Not recorded | 517.8 | 517.8 | Not recorded | 4,216.9 | 5,240 |
| 244.5 | 64.74 | T-95 | 517.8 | Not recorded | 517.8 | 517.8 | Not recorded | 4,216.9 | 5,240 |
| 244.5 | 64.74 | P-110 | 599.8 | Not recorded | 599.8 | 599.8 | Not recorded | 4,919.7 | 6,174.1 |
| 244.5 | 64.74 | Q-125 | 681.9 | Not recorded | 681.9 | 681.9 | Not recorded | 5,515.8 | 6,792.4 |
| 244.5 | 69.94 | L-80 | 473.7 | Not recorded | 473.7 | 473.7 | Not recorded | 3,972.3 | 4,990.9 |
| 244.5 | 69.94 | N-80 | 473.7 | Not recorded | 473.7 | 473.7 | Not recorded | 4,025.6 | 5,164.4 |
| 244.5 | 69.94 | C-90 | 532.3 | Not recorded | 532.3 | 532.3 | Not recorded | 4,390.4 | 5,382.3 |
| 244.5 | 69.94 | C-95 | 561.9 | Not recorded | 561.9 | 561.9 | Not recorded | 4,626.2 | 5,662.6 |
| 244.5 | 69.94 | T-95 | 561.9 | Not recorded | 561.9 | 561.9 | Not recorded | 4,626.2 | 5,662.6 |
| 244.5 | 69.94 | P-110 | 650.9 | Not recorded | 650.9 | 650.9 | Not recorded | 5,395.7 | 6,672.3 |
| 244.5 | 69.94 | Q-125 | 739.8 | Not recorded | 739.8 | 739.8 | Not recorded | 6,054 | 7,339.6 |

Check every figure against your own pipe records before you pull.

# Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 2 of 2: internal yield and joint strength

| OD mm | Weight kg/m | Grade | Internal yield PE bar | Internal yield STC bar | Internal yield LTC bar | Internal yield BTC bar | Joint STC kN | Joint LTC kN | Joint BTC kN |
|---|---|---|---|---|---|---|---|---|---|
| OD 9-5/8 in | | | | | | | | | |
| 244.5 | 79.62 | L-80 | 546.8 | Not recorded | 546.8 | 546.8 | Not recorded | 4,657.3 | 5,720.4 |
| 244.5 | 79.62 | N-80 | 546.8 | Not recorded | 546.8 | 546.8 | Not recorded | 4,724 | 5,911.7 |
| 244.5 | 79.62 | C-90 | 615 | Not recorded | 615 | 615 | Not recorded | 5,146.6 | 6,165.2 |
| 244.5 | 79.62 | C-95 | 648.8 | Not recorded | 648.8 | 648.8 | Not recorded | 5,426.8 | 6,485.5 |
| 244.5 | 79.62 | T-95 | 648.8 | Not recorded | 648.8 | 648.8 | Not recorded | 5,426.8 | 6,485.5 |
| 244.5 | 79.62 | P-110 | 751.5 | Not recorded | 751.5 | 751.5 | Not recorded | 6,325.4 | 7,642 |
| 244.5 | 79.62 | Q-125 | 854.3 | Not recorded | 854.3 | 854.3 | Not recorded | 7,094.9 | 8,407.1 |
| 244.5 | 86.91 | L-80 | 596.4 | Not recorded | 596.4 | 596.4 | Not recorded | 5,119.9 | 6,209.7 |
| 244.5 | 86.91 | N-80 | 596.4 | Not recorded | 596.4 | 596.4 | Not recorded | 5,191.1 | 6,418.8 |
| 244.5 | 86.91 | C-90 | 671.5 | Not recorded | 671.5 | 671.5 | Not recorded | 5,658.1 | 6,690.1 |
| 244.5 | 86.91 | C-95 | 708.8 | Not recorded | 708.8 | 708.8 | Not recorded | 5,965.1 | 7,041.5 |
| 244.5 | 86.91 | T-95 | 708.8 | Not recorded | 708.8 | 708.8 | Not recorded | 5,965.1 | 7,041.5 |
| 244.5 | 86.91 | P-110 | 820.5 | Not recorded | 820.5 | 820.5 | Not recorded | 6,957 | 8,295.9 |
| 244.5 | 86.91 | Q-125 | 932.2 | Not recorded | 932.2 | 932.2 | Not recorded | 7,802.2 | 9,127.8 |
| 244.5 | 88.4 | C-90 | 687.4 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 244.5 | 88.4 | T-95 | 725.3 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 244.5 | 96.58 | C-90 | 758.4 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 244.5 | 96.58 | T-95 | 800.5 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 244.5 | 104.62 | C-90 | 828.1 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 244.5 | 104.62 | T-95 | 874.3 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 244.5 | 112.51 | C-90 | 899.1 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 244.5 | 112.51 | T-95 | 949.4 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| OD 9-3/4 in | | | | | | | | | |
| 247.6 | 88.1 | P-110 | 810.1 | Not recorded | 810.1 | 810.1 | Not recorded | 6,169.7 | 7,477.5 |
| 247.6 | 88.1 | Q-125 | 920.5 | Not recorded | 920.5 | 920.5 | Not recorded | 6,917 | 8,229.2 |

Check every figure against your own pipe records before you pull.

# Casingjacks

Casingjacks LLC | sales@casingjack.com

## Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 2 of 2: internal yield and joint strength

| OD mm | Weight kg/m | Grade | Internal yield PE bar | Internal yield STC bar | Internal yield LTC bar | Internal yield BTC bar | Joint STC kN | Joint LTC kN | Joint BTC kN |
|---|---|---|---|---|---|---|---|---|---|
| OD 9-7/8 in | | | | | | | | | |
| 250.8 | 93.46 | P-110 | 839.8 | Not recorded | 839.8 | 837 | Not recorded | 5,756 | 7,046 |
| 250.8 | 93.46 | Q-125 | 954.2 | Not recorded | 954.2 | 951.5 | Not recorded | 6,454.4 | 7,753.3 |
| OD 10-3/4 in | | | | | | | | | |
| 273.1 | 48.74 | H-40 | 125.5 | 125.5 | Not recorded | Not recorded | 911.9 | Not recorded | Not recorded |
| 273.1 | 60.27 | H-40 | 157.2 | 157.2 | Not recorded | Not recorded | 1,396.7 | Not recorded | Not recorded |
| 273.1 | 60.27 | J-55 | 215.8 | 215.8 | Not recorded | 215.8 | 1,868.3 | Not recorded | 3,113.8 |
| 273.1 | 60.27 | K-55 | 215.8 | 215.8 | Not recorded | 215.8 | 2,001.7 | Not recorded | 3,643.1 |
| 273.1 | 60.27 | M-65 | 255.1 | 255.1 | Not recorded | 255.1 | 2,184.1 | Not recorded | 3,585.3 |
| 273.1 | 60.27 | N-80 | 314.4 | 314.4 | Not recorded | 314.4 | 2,655.6 | Not recorded | 4,288.1 |
| 273.1 | 67.71 | J-55 | 246.8 | 246.8 | Not recorded | 246.8 | 2,193 | Not recorded | 3,540.8 |
| 273.1 | 67.71 | M-65 | 291.6 | 291.6 | Not recorded | 291.6 | 2,562.2 | Not recorded | 4,074.6 |
| 273.1 | 67.71 | N-80 | 359.2 | 359.2 | Not recorded | 359.2 | 3,118.2 | Not recorded | 4,879.7 |
| 273.1 | 75.9 | J-55 | 277.9 | 277.9 | Not recorded | 277.9 | 2,513.2 | Not recorded | 3,963.4 |
| 273.1 | 75.9 | K-55 | 277.9 | 277.9 | Not recorded | 277.9 | 2,695.6 | Not recorded | 4,639.5 |
| 273.1 | 75.9 | M-65 | 328.2 | 328.2 | Not recorded | 328.2 | 2,940.3 | Not recorded | 4,563.9 |
| 273.1 | 75.9 | L-80 | 404 | 404 | Not recorded | 404 | 3,531.9 | Not recorded | 5,293.4 |
| 273.1 | 75.9 | N-80 | 404 | 404 | Not recorded | 404 | 3,576.4 | Not recorded | 5,462.4 |
| 273.1 | 75.9 | C-90 | 454.4 | 454.4 | Not recorded | 454.4 | 3,910 | Not recorded | 5,724.9 |
| 273.1 | 75.9 | C-95 | 479.9 | 479.9 | Not recorded | 479.9 | 4,123.5 | Not recorded | 6,022.9 |
| 273.1 | 75.9 | T-95 | 479.9 | 479.9 | Not recorded | 479.9 | 4,123.5 | Not recorded | 6,022.9 |
| 273.1 | 75.9 | P-110 | 555.7 | 555.7 | Not recorded | 555.7 | 4,804.1 | Not recorded | 7,090.5 |
| 273.1 | 75.9 | Q-125 | 631.6 | 631.6 | Not recorded | 631.6 | 5,395.7 | Not recorded | 7,820 |
| 273.1 | 82.59 | L-80 | 444.7 | 444.7 | Not recorded | 444.7 | 3,932.2 | Not recorded | 5,796 |
| 273.1 | 82.59 | N-80 | 444.7 | 444.7 | Not recorded | 444.7 | 3,981.2 | Not recorded | 5,982.9 |
| 273.1 | 82.59 | C-90 | 499.9 | 499.9 | Not recorded | 499.9 | 4,354.8 | Not recorded | 6,267.5 |

Check every figure against your own pipe records before you pull.

# Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 2 of 2: internal yield and joint strength

| OD mm | Weight kg/m | Grade | Internal yield PE bar | Internal yield STC bar | Internal yield LTC bar | Internal yield BTC bar | Joint STC kN | Joint LTC kN | Joint BTC kN |
|---|---|---|---|---|---|---|---|---|---|
| OD 10-3/4 in | | | | | | | | | |
| 273.1 | 82.59 | C-95 | 528.1 | 528.1 | Not recorded | 528.1 | 4,590.6 | Not recorded | 6,596.7 |
| 273.1 | 82.59 | T-95 | 528.1 | 528.1 | Not recorded | 528.1 | 4,590.6 | Not recorded | 6,596.7 |
| 273.1 | 82.59 | P-110 | 610.9 | 610.9 | Not recorded | 610.9 | 5,351.2 | Not recorded | 7,762.1 |
| 273.1 | 82.59 | Q-125 | 694.3 | 694.3 | Not recorded | 694.3 | 6,009.5 | Not recorded | 8,562.8 |
| 273.1 | 90.33 | L-80 | 489.5 | 489.5 | Not recorded | 489.5 | 4,372.6 | Not recorded | 6,352.1 |
| 273.1 | 90.33 | N-80 | 489.5 | 489.5 | Not recorded | 489.5 | 4,430.4 | Not recorded | 6,552.2 |
| 273.1 | 90.33 | C-90 | 550.2 | 550.2 | Not recorded | 550.2 | 4,844.1 | Not recorded | 6,868.1 |
| 273.1 | 90.33 | C-95 | 581.2 | 581.2 | Not recorded | 581.2 | 5,106.6 | Not recorded | 7,228.4 |
| 273.1 | 90.33 | T-95 | 581.2 | 581.2 | Not recorded | 581.2 | 5,106.6 | Not recorded | 7,228.4 |
| 273.1 | 90.33 | P-110 | 672.9 | 672.9 | Not recorded | 672.9 | 5,951.7 | Not recorded | 8,505 |
| 273.1 | 90.33 | Q-125 | 764.6 | 764.6 | Not recorded | 764.6 | 6,685.7 | Not recorded | 9,381.3 |
| 273.1 | 97.77 | L-80 | 534.3 | 534.3 | Not recorded | 534.3 | 4,813 | Not recorded | 6,899.2 |
| 273.1 | 97.77 | N-80 | 534.3 | 534.3 | Not recorded | 534.3 | 4,875.3 | Not recorded | 7,117.2 |
| 273.1 | 97.77 | C-90 | 601.2 | 601.2 | Not recorded | 601.2 | 5,329 | Not recorded | 7,459.7 |
| 273.1 | 97.77 | T-95 | 634.3 | 634.3 | Not recorded | 634.3 | 5,618.1 | Not recorded | 7,851.1 |
| 273.1 | 97.77 | P-110 | 734.3 | 734.3 | Not recorded | 734.3 | 6,547.8 | Not recorded | 9,239 |
| 273.1 | 97.77 | Q-125 | 835 | 835 | Not recorded | 835 | 7,352.9 | Not recorded | 10,190.9 |
| 273.1 | 105.81 | P-110 | 802.5 | 775 | Not recorded | 757 | 7,197.2 | Not recorded | 10,039.6 |
| 273.1 | 105.81 | Q-125 | 912.2 | 881.1 | Not recorded | 860.5 | 8,082.4 | Not recorded | 11,071.6 |
| 273.1 | 108.93 | C-90 | 679.1 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 273.1 | 108.93 | T-95 | 716.4 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 273.1 | 117.86 | C-90 | 741.2 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 273.1 | 117.86 | T-95 | 782.6 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 273.1 | 126.94 | C-90 | 805.3 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |
| 273.1 | 126.94 | T-95 | 850.1 | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded | Not recorded |

Check every figure against your own pipe records before you pull.

# Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 2 of 2: internal yield and joint strength

| OD mm | Weight kg/m | Grade | Internal yield PE bar | Internal yield STC bar | Internal yield LTC bar | Internal yield BTC bar | Joint STC kN | Joint LTC kN | Joint BTC kN |
|---|---|---|---|---|---|---|---|---|---|
| OD 11-3/4 in | | | | | | | | | |
| 298.4 | 62.5 | H-40 | 136.5 | 136.5 | Not recorded | 136.5 | 1,365.6 | Not recorded | 2,464.3 |
| 298.4 | 69.94 | J-55 | 211.7 | Not recorded | 211.7 | 211.7 | 2,121.8 | Not recorded | 3,589.7 |
| 298.4 | 69.94 | K-55 | 211.7 | Not recorded | 211.7 | 211.7 | 2,264.1 | Not recorded | 4,159.1 |
| 298.4 | 69.94 | M-65 | 250.3 | Not recorded | 250.3 | 250.3 | 2,477.7 | Not recorded | 4,141.3 |
| 298.4 | 80.36 | J-55 | 245.5 | Not recorded | 245.5 | 245.5 | 2,526.6 | Not recorded | 4,141.3 |
| 298.4 | 80.36 | K-55 | 245.5 | Not recorded | 245.5 | 245.5 | 2,695.6 | Not recorded | 4,799.6 |
| 298.4 | 80.36 | M-65 | 290.3 | Not recorded | 290.3 | 290.3 | 2,958.1 | Not recorded | 4,777.4 |
| 298.4 | 89.29 | J-55 | 276.5 | 276.5 | Not recorded | 276.5 | 2,886.9 | Not recorded | 4,635 |
| 298.4 | 89.29 | K-55 | 276.5 | 276.5 | Not recorded | 276.5 | 3,082.6 | Not recorded | 5,373.5 |
| 298.4 | 89.29 | M-65 | 326.1 | 326.1 | Not recorded | 326.1 | 3,376.2 | Not recorded | 5,342.3 |
| 298.4 | 89.29 | L-80 | 402 | 402 | Not recorded | 402 | 4,061.2 | Not recorded | 6,223.1 |
| 298.4 | 89.29 | N-80 | 402 | 402 | Not recorded | 402 | 4,110.2 | Not recorded | 6,405.4 |
| 298.4 | 89.29 | C-90 | 451.6 | 451.6 | Not recorded | 451.6 | 4,497.2 | Not recorded | 6,748 |
| 298.4 | 89.29 | C-95 | 477.1 | 477.1 | Not recorded | 477.1 | 4,741.8 | Not recorded | 7,099.4 |
| 298.4 | 89.29 | T-95 | 477.1 | 477.1 | Not recorded | 477.1 | 4,741.8 | Not recorded | 7,099.4 |
| 298.4 | 89.29 | P-110 | 552.3 | 552.3 | Not recorded | 552.3 | 5,524.7 | Not recorded | 8,349.3 |
| 298.4 | 89.29 | Q-125 | 627.4 | 627.4 | Not recorded | 627.4 | 6,209.7 | Not recorded | 9,225.6 |
| 298.4 | 96.73 | M-65 | 356.5 | 356.5 | Not recorded | 356.5 | 3,723.2 | Not recorded | 5,813.8 |
| 298.4 | 96.73 | L-80 | 438.5 | 438.5 | Not recorded | 438.5 | 4,479.4 | Not recorded | 6,765.7 |
| 298.4 | 96.73 | N-80 | 438.5 | 438.5 | Not recorded | 438.5 | 4,532.7 | Not recorded | 6,965.9 |
| 298.4 | 96.73 | P-110 | 603.3 | 603.3 | Not recorded | 603.3 | 6,098.5 | Not recorded | 9,078.8 |
| 298.4 | 96.73 | Q-125 | 685.3 | 685.3 | Not recorded | 685.3 | 6,850.3 | Not recorded | 10,035.2 |
| 298.4 | 105.66 | Q-125 | 747.4 | 747.4 | Not recorded | 747.4 | 7,530.8 | Not recorded | 10,889.2 |
| OD 11-7/8 in | | | | | | | | | |
| 301.6 | 106.85 | P-110 | 650.2 | 650.2 | Not recorded | 650.2 | 5,911.7 | Not recorded | 8,843.1 |

Check every figure against your own pipe records before you pull.

# Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 2 of 2: internal yield and joint strength

| OD mm | Weight kg/m | Grade | Internal yield PE bar | Internal yield STC bar | Internal yield LTC bar | Internal yield BTC bar | Joint STC kN | Joint LTC kN | Joint BTC kN |
|---|---|---|---|---|---|---|---|---|---|
| OD 11-7/8 in | | | | | | | | | |
| 301.6 | 106.85 | Q-125 | 739.1 | 739.1 | Not recorded | 739.1 | 6,645.6 | Not recorded | 9,777.2 |
| OD 13-3/8 in | | | | | | | | | |
| 339.7 | 71.43 | H-40 | 119.3 | 119.3 | Not recorded | 119.3 | 1,432.3 | Not recorded | 2,700.1 |
| 339.7 | 81.1 | J-55 | 188.2 | 188.2 | Not recorded | 188.2 | 2,286.4 | Not recorded | 4,043.4 |
| 339.7 | 81.1 | K-55 | 188.2 | 188.2 | Not recorded | 188.2 | 2,433.2 | Not recorded | 4,617.3 |
| 339.7 | 81.1 | M-65 | 222.7 | 222.7 | Not recorded | 222.7 | 2,677.8 | Not recorded | 4,679.5 |
| 339.7 | 90.78 | J-55 | 213 | 213 | Not recorded | 213 | 2,646.7 | Not recorded | 4,559.4 |
| 339.7 | 90.78 | K-55 | 213 | 213 | Not recorded | 213 | 2,815.7 | Not recorded | 5,200 |
| 339.7 | 90.78 | M-65 | 252.3 | 252.3 | Not recorded | 252.3 | 3,100.4 | Not recorded | 5,271.1 |
| 339.7 | 101.2 | J-55 | 237.9 | 237.9 | Not recorded | 237.9 | 3,002.5 | Not recorded | 5,071 |
| 339.7 | 101.2 | K-55 | 237.9 | 237.9 | Not recorded | 237.9 | 3,193.8 | Not recorded | 5,782.7 |
| 339.7 | 101.2 | M-65 | 281.3 | 281.3 | Not recorded | 281.3 | 3,518.5 | Not recorded | 5,862.8 |
| 339.7 | 101.2 | L-80 | 346.1 | 346.1 | Not recorded | 346.1 | 4,234.7 | Not recorded | 6,872.5 |
| 339.7 | 101.2 | N-80 | 346.1 | 346.1 | Not recorded | 346.1 | 4,283.6 | Not recorded | 7,050.4 |
| 339.7 | 101.2 | C-90 | 389.6 | 389.6 | Not recorded | 389.6 | 4,701.8 | Not recorded | 7,486.4 |
| 339.7 | 101.2 | C-95 | 411.6 | 411.6 | Not recorded | 411.6 | 4,955.3 | Not recorded | 7,882.2 |
| 339.7 | 101.2 | T-95 | 411.6 | 411.6 | Not recorded | 411.6 | 4,955.3 | Not recorded | 7,882.2 |
| 339.7 | 101.2 | P-110 | 476.4 | 476.4 | Not recorded | 476.4 | 5,769.3 | Not recorded | 9,247.9 |
| 339.7 | 107.15 | M-65 | 301.3 | 301.3 | Not recorded | 301.3 | 3,798.8 | Not recorded | 6,263.1 |
| 339.7 | 107.15 | L-80 | 370.9 | 370.9 | Not recorded | 370.9 | 4,577.2 | Not recorded | 7,339.6 |
| 339.7 | 107.15 | N-80 | 370.9 | 370.9 | Not recorded | 370.9 | 4,626.2 | Not recorded | 7,530.8 |
| 339.7 | 107.15 | C-90 | 417.1 | 417.1 | Not recorded | 417.1 | 5,079.9 | Not recorded | 7,997.9 |
| 339.7 | 107.15 | C-95 | 440.6 | 440.6 | Not recorded | 440.6 | 5,355.7 | Not recorded | 8,420.5 |
| 339.7 | 107.15 | T-95 | 440.6 | 440.6 | Not recorded | 440.6 | 5,355.7 | Not recorded | 8,420.5 |
| 339.7 | 107.15 | P-110 | 510.2 | 510.2 | Not recorded | 510.2 | 6,236.4 | Not recorded | 9,879.5 |

Check every figure against your own pipe records before you pull.

# Casingjacks

Casingjacks LLC | sales@casingjack.com

## Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 2 of 2: internal yield and joint strength

| OD mm | Weight kg/m | Grade | Internal yield PE bar | Internal yield STC bar | Internal yield LTC bar | Internal yield BTC bar | Joint STC kN | Joint LTC kN | Joint BTC kN |
|---|---|---|---|---|---|---|---|---|---|
| OD 13-3/8 in | | | | | | | | | |
| 339.7 | 107.15 | Q-125 | 579.8 | 579.8 | Not recorded | 579.8 | 7,014.8 | Not recorded | 10,956 |
| 339.7 | 120.09 | P-110 | 575.7 | Not recorded | Not recorded | 575.7 | Not recorded | Not recorded | 11,089.4 |
| 339.7 | 120.09 | Q-125 | 654.3 | Not recorded | Not recorded | 654.3 | Not recorded | Not recorded | 12,299.3 |
| 339.7 | 127.98 | P-110 | 620.5 | Not recorded | Not recorded | 619.1 | Not recorded | Not recorded | 11,907.9 |
| 339.7 | 127.98 | Q-125 | 704.6 | Not recorded | Not recorded | 703.3 | Not recorded | Not recorded | 13,206.8 |
| OD 13-1/2 in | | | | | | | | | |
| 342.9 | 121.14 | P-110 | 570.2 | Not recorded | Not recorded | 570.2 | Not recorded | Not recorded | 9,941.8 |
| 342.9 | 121.14 | Q-125 | 648.1 | Not recorded | Not recorded | 648.1 | Not recorded | Not recorded | 11,027.1 |
| OD 13-5/8 in | | | | | | | | | |
| 346.1 | 131.26 | P-110 | 608.8 | Not recorded | Not recorded | 608.8 | Not recorded | Not recorded | 9,621.5 |
| 346.1 | 131.26 | Q-125 | 691.5 | Not recorded | Not recorded | 691.5 | Not recorded | Not recorded | 10,671.3 |
| OD 16 in | | | | | | | | | |
| 406.4 | 96.73 | H-40 | 113.1 | 113.1 | Not recorded | 113.1 | 1,952.8 | Not recorded | 3,474.1 |
| 406.4 | 111.61 | J-55 | 181.3 | 181.3 | Not recorded | 181.3 | 3,158.2 | Not recorded | 5,337.9 |
| 406.4 | 111.61 | K-55 | 181.3 | 181.3 | Not recorded | 181.3 | 3,345.1 | Not recorded | 5,920.6 |
| 406.4 | 111.61 | M-65 | 214.4 | 214.4 | Not recorded | 214.4 | 3,700.9 | Not recorded | 6,200.8 |
| 406.4 | 125.01 | J-55 | 205.5 | 205.5 | Not recorded | 205.5 | 3,634.2 | Not recorded | 6,009.5 |
| 406.4 | 125.01 | K-55 | 205.5 | 205.5 | Not recorded | 205.5 | 3,847.7 | Not recorded | 6,667.9 |
| 406.4 | 125.01 | M-65 | 242.7 | 242.7 | Not recorded | 242.7 | 4,256.9 | Not recorded | 6,983.7 |
| 406.4 | 125.01 | N-80 | 298.5 | 298.5 | Not recorded | 298.5 | 5,191.1 | Not recorded | 8,442.7 |
| 406.4 | 125.01 | P-110 | 410.9 | 410.9 | Not recorded | 410.9 | 7,005.9 | Not recorded | 11,200.6 |
| 406.4 | 125.01 | Q-125 | 466.8 | 466.8 | Not recorded | 466.8 | 7,886.7 | Not recorded | 12,495.1 |
| 406.4 | 141.38 | N-80 | 341.3 | Not recorded | Not recorded | 341.3 | Not recorded | Not recorded | 9,612.6 |
| 406.4 | 141.38 | P-110 | 469.5 | Not recorded | Not recorded | 469.5 | Not recorded | Not recorded | 12,748.6 |
| 406.4 | 141.38 | Q-125 | 533.7 | Not recorded | Not recorded | 533.7 | Not recorded | Not recorded | 14,225.4 |

Check every figure against your own pipe records before you pull.

# Casingjacks

Casingjacks LLC | sales@casingjack.com

## Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 2 of 2: internal yield and joint strength

| OD mm | Weight kg/m | Grade | Internal yield PE bar | Internal yield STC bar | Internal yield LTC bar | Internal yield BTC bar | Joint STC kN | Joint LTC kN | Joint BTC kN |
|---|---|---|---|---|---|---|---|---|---|
| OD 16 in | | | | | | | | | |
| 406.4 | 144.35 | N-80 | 346.8 | Not recorded | Not recorded | 346.8 | Not recorded | Not recorded | 9,759.4 |
| 406.4 | 144.35 | P-110 | 477.1 | Not recorded | Not recorded | 477.1 | Not recorded | Not recorded | 12,944.3 |
| 406.4 | 144.35 | Q-125 | 541.9 | Not recorded | Not recorded | 541.9 | Not recorded | Not recorded | 14,438.9 |
| 406.4 | 162.21 | J-55 | 272.3 | 272.3 | Not recorded | 272.3 | 4,964.2 | Not recorded | 7,882.2 |
| 406.4 | 162.21 | K-55 | 272.3 | 272.3 | Not recorded | 272.3 | 5,253.3 | Not recorded | 8,740.8 |
| 406.4 | 162.21 | N-80 | 395.8 | 395.8 | Not recorded | 395.8 | 7,090.5 | Not recorded | 11,071.6 |
| 406.4 | 175.6 | J-55 | 296.5 | 296.5 | Not recorded | 296.5 | 5,444.6 | Not recorded | 8,558.4 |
| 406.4 | 175.6 | K-55 | 296.5 | 296.5 | Not recorded | 296.5 | 5,764.9 | Not recorded | 9,479.2 |
| 406.4 | 175.6 | N-80 | 431.6 | 431.6 | Not recorded | 431.6 | 7,744.4 | Not recorded | 12,023.5 |
| OD 18-5/8 in | | | | | | | | | |
| 473.1 | 130.21 | H-40 | 112.4 | 112.4 | Not recorded | 112.4 | 2,486.6 | Not recorded | 4,417.1 |
| 473.1 | 130.21 | J-55 | 155.1 | 155.1 | Not recorded | 155.1 | 3,354 | Not recorded | 5,911.7 |
| 473.1 | 130.21 | K-55 | 155.1 | 155.1 | Not recorded | 155.1 | 3,531.9 | Not recorded | 6,347.6 |
| 473.1 | 130.21 | N-80 | 225.5 | 225.5 | Not recorded | 225.5 | 4,799.6 | Not recorded | 8,393.8 |
| 473.1 | 140.63 | H-40 | 121.3 | 121.3 | Not recorded | 121.3 | 2,709 | Not recorded | 4,746.3 |
| 473.1 | 140.63 | J-55 | 166.9 | 166.9 | Not recorded | 166.9 | 3,652 | Not recorded | 6,347.6 |
| 473.1 | 140.63 | K-55 | 166.9 | 166.9 | Not recorded | 166.9 | 3,847.7 | Not recorded | 6,819.1 |
| 473.1 | 140.63 | N-80 | 242.7 | 242.7 | Not recorded | 242.7 | 5,222.2 | Not recorded | 9,016.5 |
| 473.1 | 157.75 | J-55 | 188.9 | 188.9 | Not recorded | 188.9 | 4,216.9 | Not recorded | 7,175 |
| 473.1 | 157.75 | K-55 | 188.9 | 188.9 | Not recorded | 188.9 | 4,439.3 | Not recorded | 7,708.8 |
| 473.1 | 157.75 | N-80 | 275.1 | 275.1 | Not recorded | 275.1 | 6,031.8 | Not recorded | 10,195.3 |
| 473.1 | 174.86 | J-55 | 211 | 211 | Not recorded | 211 | 4,768.5 | Not recorded | 7,984.6 |
| 473.1 | 174.86 | K-55 | 211 | 211 | Not recorded | 211 | 5,022 | Not recorded | 8,580.6 |
| 473.1 | 174.86 | N-80 | 307.5 | 307.5 | Not recorded | 307.5 | 6,823.6 | Not recorded | 11,347.4 |

Check every figure against your own pipe records before you pull.

# Casingjacks

Casingjacks LLC | sales@casingjack.com

## Casing data book metric

Data version 1.326cfcf0 | Build date 2026-11-17

Casing data metric, part 2 of 2: internal yield and joint strength

| OD mm | Weight kg/m | Grade | Internal yield PE bar | Internal yield STC bar | Internal yield LTC bar | Internal yield BTC bar | Joint STC kN | Joint LTC kN | Joint BTC kN |
|---|---|---|---|---|---|---|---|---|---|
| OD 20 in | | | | | | | | | |
| 508 | 139.89 | H-40 | 105.5 | 105.5 | Not recorded | 105.5 | 2,584.4 | Not recorded | 4,630.6 |
| 508 | 139.89 | J-55 | 145.5 | 145.5 | 145.5 | 145.5 | 3,483 | 4,034.5 | 6,236.4 |
| 508 | 139.89 | K-55 | 145.5 | 145.5 | 145.5 | 145.5 | 3,665.3 | 4,248.1 | 6,578.9 |
| 508 | 158.49 | J-55 | 166.2 | 166.2 | 166.2 | 166.2 | 4,061.2 | 4,697.3 | 7,094.9 |
| 508 | 158.49 | K-55 | 166.2 | 166.2 | 166.2 | 166.2 | 4,270.3 | 4,950.9 | 7,486.4 |
| 508 | 158.49 | N-80 | 241.3 | 241.3 | 241.3 | 241.3 | 5,813.8 | 6,734.6 | 10,146.4 |
| 508 | 197.93 | K-55 | 211 | 211 | 211 | 211 | 5,573.6 | 6,463.3 | 9,443.6 |
| 508 | 197.93 | L-80 | 306.8 | 306.8 | 306.8 | 306.8 | 7,526.4 | 8,709.6 | 12,673 |
| 508 | 197.93 | N-80 | 306.8 | 306.8 | 306.8 | 306.8 | 7,593.1 | 8,789.7 | 12,797.5 |
| 508 | 251.5 | K-55 | 269.6 | 222.7 | 236.5 | 233 | 6,236.4 | 7,704.3 | 11,961.3 |
| 508 | 251.5 | L-80 | 391.6 | 323.4 | 344 | 339.2 | 9,795 | 11,338.5 | 16,058.1 |
| 508 | 251.5 | N-80 | 391.6 | 323.4 | 344 | 339.2 | 9,879.5 | 11,445.3 | 16,213.8 |

Check every figure against your own pipe records before you pull.